



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
BUS 704
 Component
Diesel Engine
 Fluid
CHEVRON DELO 400 LE 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DC0037509	DC0031898	DC0028373
Sample Date		Client Info		03 Jul 2024	01 Feb 2024	10 Jul 2023
Machine Age	mls	Client Info		92592	76871	61645
Oil Age	mls	Client Info		0	0	0
Filter Age	mls	Client Info		0	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	16	20	20
Chromium	ppm	ASTM D5185m	>20	1	2	1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	4	4	3
Lead	ppm	ASTM D5185m	>40	0	0	0
Copper	ppm	ASTM D5185m	>330	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	4	6	5
Potassium	ppm	ASTM D5185m	>20	2	1	2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	1.2	0.6	1.3
Nitration	Abs/cm	*ASTM D7624	>20	8.1	7.2	8.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.4	19.4	24.4
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<1	1	<1
Boron	ppm	ASTM D5185m		216	240	230
Barium	ppm	ASTM D5185m		0	0	2
Molybdenum	ppm	ASTM D5185m		82	76	87
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		382	367	401
Calcium	ppm	ASTM D5185m		1482	1304	1453
Phosphorus	ppm	ASTM D5185m	1200	1035	937	1030
Zinc	ppm	ASTM D5185m	1300	1239	1165	1285
Sulfur	ppm	ASTM D5185m	3200	2933	2966	3420
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.1	13.5	16.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	6.2	6.6	7.3
Visc @ 100°C	cSt	ASTM D445	15.7	13.8	13.4	14.2



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DC0037509 **Received** : 12 Jul 2024
Lab Number : 06234647 **Tested** : 15 Jul 2024
Unique Number : 11123481 **Diagnosed** : 15 Jul 2024 - Don Baldrige
Test Package : MOB 1 (Additional Tests: TBN)

KELLER BUS
 4472 GALLANT GREEN RD
 WALDORF, MD
 US 20601
 Contact: Paul Or Larry
 Lking@kellerbus.com
 T: (301)645-5734
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)