



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
MIXERS
Machine Id
[MIXERS] M203
Component
Diesel Engine
Fluid
KENDALL 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LP0001272	PCA0109792	LP0000666
Sample Date		Client Info		03 Jul 2024	08 Apr 2024	30 Oct 2023
Machine Age	hrs	Client Info		40162	40162	39585
Oil Age	hrs	Client Info		600	600	600
Filter Age	hrs	Client Info		600	600	600
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	26	51	39
Chromium	ppm	ASTM D5185m	>20	<1	2	<1
Nickel	ppm	ASTM D5185m	>4	0	<1	0
Titanium	ppm	ASTM D5185m		<1	1	1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	3	3	2
Lead	ppm	ASTM D5185m	>40	3	5	2
Copper	ppm	ASTM D5185m	>330	5	19	26
Tin	ppm	ASTM D5185m	>15	2	3	1
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	5	7	5
Potassium	ppm	ASTM D5185m	>20	1	2	<1
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	2.3	▲ 3.4	0.2
Nitration	Abs/cm	*ASTM D7624	>20	10.3	12.1	9.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1	26.5	24.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		3	5	5
Boron	ppm	ASTM D5185m	6.3	43	34	30
Barium	ppm	ASTM D5185m	0.6	0	0	0
Molybdenum	ppm	ASTM D5185m	0.4	87	98	81
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	277	68	153	197
Calcium	ppm	ASTM D5185m	1514	2254	2354	1889
Phosphorus	ppm	ASTM D5185m	634	1082	1106	966
Zinc	ppm	ASTM D5185m	743	1301	1302	1193
Sulfur	ppm	ASTM D5185m	2592	4494	3796	3102
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.4	17.6	21.2
Base Number (BN)	mg KOH/g	ASTM D2896		8.78	7.43	8.18
Visc @ 100°C	cSt	ASTM D445		13.8	13.8	14.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LP0001272 **Received** : 12 Jul 2024
Lab Number : 06235123 **Tested** : 15 Jul 2024
Unique Number : 11123957 **Diagnosed** : 15 Jul 2024 - Wes Davis
Test Package : MOB 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

CONSTRUCTION SERVICES
 2420 BOSTON RD
 WILBRAHAM, MA
 US 01095
 Contact: Michael Dupuis
 mdupuis@cs-ma.us
 T: (413)733-6331
 F: