WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL



VOLVO A30G 340072
Component
Front Left Final Drive
Fluid

GEAR OIL SAE 80W140 (--- GAL)

GEAR OIL SAE 80W 140 ( GA	<b>∟)</b>						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ML0946571		
resample at the next service interval to monitor.	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		11600		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAD							
WEAR	Iron	ppm	ASTM D5185m		42		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>30	3		
	Lead	ppm	ASTM D5185m	>50	0		
	Copper	ppm	ASTM D5185m	>150	4		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	4		
	Potassium	ppm	ASTM D5185m		1		
There is no indication of any contamination in the oil.	Water	1-1-	WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m	400	167		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		<1		
	Molybdenum	ppm	ASTM D5185m		1		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	12	12		
	Calcium	ppm	ASTM D5185m		85		
	Phosphorus	ppm	ASTM D5185m		1077		
	Zinc	ppm	ASTM D5185m		53		
	Sulfur	ppm	ASTM D5185m		28694		
	Visc @ 40°C	cSt	ASTM D445		290		
	1100 @ 40 0	001	. 10 1111 0 170	_00		,	





Certificate L2367

Laboratory

Sample No.

: ML0946571 Lab Number : 06235265 Unique Number : 11124099 Test Package : MOB 1

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 12 Jul 2024 **Tested** : 15 Jul 2024

Diagnosed : 15 Jul 2024 - Sean Felton

Contact: SERVICE MANAGER jimmy\_elswick@wahazel.com

T: (703)378-8300

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**WILLIAM HAZEL** 

CHANTILLY, VA

PO BOX 600

US 20153

F: