



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
AMR-Cheyenne
 Machine Id
439142 SENNEBOGEN 840E 840.0.2133
 Component
Rear Left Planetary
 Fluid
CHEVRON DELO GEAR ESI OIL 80W90 (3 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		DJJ0023965	DJJ0023241	DJJ0019107
Sample Date		Client Info		24 Jun 2024	13 Mar 2024	05 Dec 2023
Machine Age	hrs	Client Info		13360	12659	12141
Oil Age	hrs	Client Info		500	1000	500
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changed	Changed	Not Changed
Filter Changed		Client Info		Not Changed	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>500	6	10	7
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>25	3	<1	3
Lead	ppm	ASTM D5185m	>25	0	1	0
Copper	ppm	ASTM D5185m	>75	1	1	2
Tin	ppm	ASTM D5185m	>10	0	2	0
Vanadium	ppm	ASTM D5185m		<1	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	1	1	<1
Potassium	ppm	ASTM D5185m	>20	1	1	<1
Water		WC Method	>0.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	LIGHT	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	2	0
Boron	ppm	ASTM D5185m	15	105	173	207
Barium	ppm	ASTM D5185m	0	<1	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	0	2	0	<1
Calcium	ppm	ASTM D5185m	5	0	1	4
Phosphorus	ppm	ASTM D5185m	600	864	1000	976
Zinc	ppm	ASTM D5185m	0	6	0	0
Sulfur	ppm	ASTM D5185m	22000	17361	20005	19126
Visc @ 40°C	cSt	ASTM D445	140	139	141	139



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : DJJ0023965
Lab Number : 06235271
Unique Number : 11124105
Test Package : CONST

Received : 12 Jul 2024
Tested : 15 Jul 2024
Diagnosed : 15 Jul 2024 - Wes Davis

ADVANTAGE METALS RECYCLING - CHEYENNE
 1015 S. PACKARD ST
 KANSAS CITY, KS
 US 66105
 Contact: BRIAN JACOBS
 BRIAN.JACOBS@ADVANTAGERECYCLING.COM
 T: (816)808-4711
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)