



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

THOMAS HATTAN - 586790 [312]

Machine Id

KOHLER 336KGM1K003

Component

Port Genset

Fluid

VOLVO ULTRA DIESEL ENGINE OIL 15W40 VDS-3 (2 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		VPA044528	---	---
Sample Date		Client Info		11 Jul 2024	---	---
Machine Age	hrs	Client Info		43	---	---
Oil Age	hrs	Client Info		43	---	---
Filter Age	hrs	Client Info		0	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				NORMAL	---	---

WEAR

Metal levels are typical for a new component breaking in.

Iron	ppm	ASTM D5185m	>50	8	---	---
Chromium	ppm	ASTM D5185m	>4	0	---	---
Nickel	ppm	ASTM D5185m	>2	0	---	---
Titanium	ppm	ASTM D5185m		0	---	---
Silver	ppm	ASTM D5185m	>5	0	---	---
Aluminum	ppm	ASTM D5185m	>12	<1	---	---
Lead	ppm	ASTM D5185m	>17	0	---	---
Copper	ppm	ASTM D5185m	>70	3	---	---
Tin	ppm	ASTM D5185m	>15	0	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	15	---	---
Potassium	ppm	ASTM D5185m	>20	3	---	---
Fuel		WC Method	>4.0	<1.0	---	---
Water		WC Method	>0.1	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844		0	---	---
Nitration	Abs/cm	*ASTM D7624	>20	5.9	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.8	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.1	NEG	---	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		5	---	---
Boron	ppm	ASTM D5185m	2.5	137	---	---
Barium	ppm	ASTM D5185m	0.0	1	---	---
Molybdenum	ppm	ASTM D5185m	0.7	5	---	---
Manganese	ppm	ASTM D5185m	0.0	3	---	---
Magnesium	ppm	ASTM D5185m	256	661	---	---
Calcium	ppm	ASTM D5185m	2057	1478	---	---
Phosphorus	ppm	ASTM D5185m	935	1016	---	---
Zinc	ppm	ASTM D5185m	1223	1188	---	---
Sulfur	ppm	ASTM D5185m	4079	4894	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	12.1	---	---
Base Number (BN)	mg KOH/g	ASTM D2896	10	8.5	---	---
Visc @ 100°C	cSt	ASTM D445	15.0	14.6	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : VPA044528 **Received** : 15 Jul 2024
Lab Number : 06235446 **Tested** : 15 Jul 2024
Unique Number : 11124280 **Diagnosed** : 15 Jul 2024 - Sean Felton
Test Package : MOB 1 (Additional Tests: TBN)

Galati Yacht Sales LLC
 900 S. BAY BLVD., PO Box 862
 ANNA MARIA, FL
 US 34216
 Contact: ERIC STAMMER
 estammer@galatiyachts.com
 T: (941)778-0755
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)