WEAR CONTAMINATION FLUID CONDITION


NORMAL ABNORMAL NORMAL

STEAM AND POWER

269.0080 #1 BOILER FEED WATER PUMP BOWSER

Bearing Lube

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		PE0001502	PE0002940	PE000141
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Date		Client Info		09 Jul 2024	30 Nov 2023	20 Sep 202
	Machine Age	hrs	Client Info		0	0	0
	Oil Age	hrs	Client Info		0	0	0
	Filter Age	hrs	Client Info		0	0	0
	Oil Changed		Client Info		N/A	N/A	N/A
	Filter Changed		Client Info		N/A	N/A	N/A
	Sample Status				ABNORMAL	ATTENTION	NORMAL
WEAR	PQ		ASTM D8184		19	11	12
	Iron	ppm	ASTM D5185m	>120	2	0	1
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>5	<1	0	0
	Nickel	ppm	ASTM D5185m	>20	0	0	0
	Titanium	ppm	ASTM D5185m		<1	0	0
	Silver	ppm	ASTM D5185m		<1	0	0
	Aluminum	ppm	ASTM D5185m	>4	3	0	2
	Lead	ppm	ASTM D5185m	>30	0	0	<1
	Copper	ppm	ASTM D5185m	>17	3	0	<1
	Tin	ppm	ASTM D5185m	>10	<1	0	0
	Vanadium	ppm	ASTM D5185m		<1	0	0
	White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
CONTAMINATION	Silicon	ppm	ASTM D5185m	>25	1	2	3
	Potassium	ppm	ASTM D5185m	>20	1	0	<1
There is a high amount of silt (particulates < 14 microns in size) present in the oil.	Water		WC Method	>0.2	NEG	NEG	NEG
	Particles >4µm		ASTM D7647	>640	1442	15321	3014
	Particles >6µm		ASTM D7647	>160	430	4510	969
	Particles >14μm		ASTM D7647	>40	25	300	117
	Particles >21μm		ASTM D7647	>10	4	9 79	42
	Particles >38μm		ASTM D7647	>3	0	5	5
	Particles >71μm		ASTM D7647		0	0	0
	Oil Cleanliness		ISO 4406 (c)		18/16/12	21/19/15	19/17/1
	Silt	scalar	*Visual	NONE	NONE	NONE	NONE
	Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
	Appearance	scalar	*Visual	NORML	NORML	NORML	NORM
	Odor	scalar	*Visual	NORML	NORML	NORML	NORM
	Emulsified Water	scalar	^Visual	>0.2	NEG	NEG	NEG
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0	0	1
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0	0	0
	Barium	ppm	ASTM D5185m		<1	0	0
	Molybdenum	ppm	ASTM D5185m		3	0	0
	Manganese	ppm	ASTM D5185m		0	0	0
	Magnesium	ppm	ASTM D5185m		30	<1	1
	Calcium	ppm	ASTM D5185m		25	<1	19
	Phosphorus	ppm	ASTM D5185m		249	305	287
	Zinc	ppm	ASTM D5185m		38	0	13
	Sulfur	ppm	ASTM D5185m		691	653	788
	Acid Number (AN)	mg KOH/g	ASTM D8045	22	0.66	0.75	0.72
	Visc @ 40°C	cSt	ASTM D445	68	68.1	69.6	69.8





Certificate L2367

Laboratory Sample No. Lab Number

: 06235765 Unique Number : 11124599

: PE0001502

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested**

: 16 Jul 2024 Diagnosed

: 16 Jul 2024 - Don Baldridge Test Package: PLANT (Additional Tests: ICP, KV40, PQ, PrtCount, SCREEN)

: 15 Jul 2024

100 Mill Rd Port Townsend, WA US 98368 Contact: LONNIE LOREE lonnie.loree@ptpc.com T: (907)738-6506

Port Townsend Paper Corporation

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)