



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	ABNORMAL



Area
Store 5 - Cross Lanes
 Machine Id
JOHN DEERE 300GL E-61 (S/N 1FF300GXEJF730870)
 Component
Hydraulic System
 Fluid
HITACHI HYDRAULIC SUPER EX 46HN (--- GAL)

RECOMMENDATION

Recommend drain oil if not already done. Reduce drain interval to 2000 hours or drain and flush and use recommended zinc free oil.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LEC0049403	LEC0024421	LEC0026602
Sample Date		Client Info		10 Jun 2024	10 Feb 2023	03 Oct 2022
Machine Age	hrs	Client Info		4974	4439	4044
Oil Age	hrs	Client Info		0	4439	0
Filter Age	hrs	Client Info		247	500	0
Oil Changed		Client Info		Not Changed	Not Changed	Not Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	19	6	10
Iron	ppm	ASTM D5185m	>32	13	11	8
Chromium	ppm	ASTM D5185m	>9	<1	<1	0
Nickel	ppm	ASTM D5185m	>5	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		<1	0	0
Aluminum	ppm	ASTM D5185m	>9	3	2	2
Lead	ppm	ASTM D5185m	>28	<1	<1	0
Copper	ppm	ASTM D5185m	>50	3	2	2
Tin	ppm	ASTM D5185m	>5	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The amount and size of particulates present in the system are acceptable.

Silicon	ppm	ASTM D5185m	>11	5	4	4
Potassium	ppm	ASTM D5185m	>20	2	<1	2
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	1114	14762	5062
Particles >6µm		ASTM D7647	>20000	167	1198	753
Particles >14µm		ASTM D7647	>640	9	6	45
Particles >21µm		ASTM D7647	>160	2	1	8
Particles >38µm		ASTM D7647	>40	0	0	1
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>23/21/16	17/15/10	21/17/10	20/17/13
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

Zinc level above manufacturer's recommendations. The AN level is acceptable for this fluid.

Sodium	ppm	ASTM D5185m	>21	0	0	0
Boron	ppm	ASTM D5185m		<1	<1	2
Barium	ppm	ASTM D5185m		<1	0	0
Molybdenum	ppm	ASTM D5185m		1	1	<1
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		14	14	13
Calcium	ppm	ASTM D5185m		54	59	50
Phosphorus	ppm	ASTM D5185m	827	386	443	418
Zinc	ppm	ASTM D5185m	0	▲ 140	▲ 142	▲ 98
Sulfur	ppm	ASTM D5185m	13	464	528	555
Acid Number (AN)	mg KOH/g	ASTM D8045	0.06	0.30	0.32	0.33
Visc @ 40°C	cSt	ASTM D445	47	44.2	44.6	45.1



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : LEC0049403 **Received** : 15 Jul 2024
Lab Number : 06235785 **Tested** : 16 Jul 2024
Unique Number : 11124619 **Diagnosed** : 16 Jul 2024 - Don Baldridge
Test Package : CONST (Additional Tests: PQ)

APEX PIPELINE
 P.O. BOX 580
 NITRO, WV
 US 25143
 Contact: KELLY TUCKER

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)