WEAR CONTAMINATION FLUID CONDITION


NORMAL NORMAL


NOT GIVEN


40420 - WRENS COLLISION


Compressor


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		UCH06236157		
	Sample Date		Client Info		31 May 2024		
	Machine Age	hrs	Client Info		715		
	Oil Age	hrs	Client Info		715		
	Filter Age	hrs	Client Info		715		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>50	0		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m	>10	0		
	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	0		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m	>50	<1		
	Tin	ppm	ASTM D5185m	>15	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m		18		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Water		WC Method	>0.1	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
<u></u>	Emulsified Water	Scalar	*Visual	>0.1	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		<1		
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		1		
	Calcium	ppm	ASTM D5185m		0		
	Phosphorus	ppm	ASTM D5185m		395		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		2342		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.071		
	Visc @ 40°C	cSt	ASTM D445		48.9		













Certificate L2367

Laboratory Sample No.

Lab Number : 06236157 Unique Number : 11124991 Test Package : IND 2

: UCH06236157

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024

Tested : 16 Jul 2024

Diagnosed

: 16 Jul 2024 - Wes Davis

ALPHARETTA, GA US 30004

Contact: ALLAN NORTON allan@gsbindustries.com

T: (678)602-0921

GSB INDUSTRIES

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)