WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL

Machine Id

JOHN DEERE 350P 1FF350PAVPF000781

Right Final Drive

GEAR OIL SAE 80W90 (--- GAL)

GEAR OIL SAE 80W90 (GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		JR0220309		
	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	>1250	21		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	5		
	Chromium	ppm	ASTM D5185m	>9	0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	0		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION							
CONTAMINATION	Silicon	ppm	ASTM D5185m		2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar scalar	*Visual	NORML >0.075	NORML NEG		
			·				
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	2		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	31		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	12	6		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		23		
	Calcium	ppm	ASTM D5185m		33		
	Phosphorus	ppm	ASTM D5185m		563		
	Zinc	ppm	ASTM D5185m		14		
	Sulfur	ppm		22500	21416		
Depart Id. IAMOLIA BAILICOADI 00000007 (Comprehe de 07/14/0004/14/74/40) Decent	Visc @ 40°C	cSt	ASTM D445		145	 ~ CLIADI.C	 TTE CUAD
Report Id: JAMCHA [WUSCAR] 06236327 (Generated: 07/16/2024 11:54:43) Rev: 1			Subn	нщеа ву	: Mike Young	y - CHAKLC	11 E SHOP





Certificate L2367

Laboratory Sample No.

: JR0220309 Lab Number : 06236327 Unique Number : 11125161

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Tested Test Package : CONST (Additional Tests: PQ)

Received : 15 Jul 2024 : 16 Jul 2024 Diagnosed

: 16 Jul 2024 - Wes Davis

JRE - CHARLOTTE 9550 STATESVILLE ROAD CHARLOTTE, NC

US 28269

Contact: CHARLOTTE SHOP myoung@jamesriverequipment.com

T: (704)597-0211

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (704)596-6198