

Machine Id JOHN DEERE 410P 1DW410PAJPFB06481 Component Center Differential Eluid

JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

| JOHN DEERE HI-GARD HID/IRANS (G/ | 4L) | | | | | | |
|---|------------------|--------|-------------|-----------|-------------|----------|----------|
| RECOMMENDATION | Test | UOM | Method | Limit/Abn | Current | History1 | History2 |
| Resample at the next service interval to monitor. | Sample Number | | Client Info | | JR0225144 | | |
| | Sample Date | | Client Info | | 12 Jul 2024 | | |
| | Machine Age | hrs | Client Info | | 2138 | | |
| | Oil Age | hrs | Client Info | | 2138 | | |
| | Filter Age | hrs | Client Info | | 0 | | |
| | Oil Changed | | Client Info | | Changed | | |
| | Filter Changed | | Client Info | | Changed | | |
| | Sample Status | | | | NORMAL | | |
| WEAR | PQ | | ASTM D8184 | | 23 | | |
| | Iron | ppm | ASTM D5185m | >500 | 42 | | |
| All component wear rates are normal. | Chromium | ppm | ASTM D5185m | >10 | <1 | | |
| | Nickel | ppm | ASTM D5185m | >10 | <1 | | |
| | Titanium | ppm | ASTM D5185m | | <1 | | |
| | Silver | ppm | ASTM D5185m | | 0 | | |
| | Aluminum | ppm | ASTM D5185m | >25 | 2 | | |
| | Lead | ppm | ASTM D5185m | >25 | 20 | | |
| | Copper | ppm | ASTM D5185m | >100 | 59 | | |
| | Tin | ppm | ASTM D5185m | >10 | 6 | | |
| | Vanadium | ppm | ASTM D5185m | | 0 | | |
| | White Metal | scalar | *Visual | NONE | NONE | | |
| | Yellow Metal | scalar | *Visual | NONE | NONE | | |
| CONTAMINATION | Silicon | ppm | ASTM D5185m | >75 | 4 | | |
| There is no indication of any contamination in the oil. | Potassium | ppm | ASTM D5185m | >20 | 3 | | |
| | Water | | WC Method | >.2 | NEG | | |
| | Silt | scalar | *Visual | NONE | NONE | | |
| | Debris | scalar | *Visual | NONE | NONE | | |
| | Sand/Dirt | scalar | *Visual | NONE | NONE | | |
| | Appearance | scalar | *Visual | NORML | NORML | | |
| | Odor | scalar | *Visual | NORML | NORML | | |
| | Emulsified Water | scalar | *Visual | >.2 | NEG | | |
| LUID CONDITION | Sodium | ppm | ASTM D5185m | | 3 | | |
| The condition of the oil is acceptable for the time in service. | Boron | ppm | ASTM D5185m | 6 | 13 | | |
| | Barium | ppm | ASTM D5185m | 0 | 2 | | |
| | Molybdenum | ppm | ASTM D5185m | 0 | 10 | | |
| | Manganese | ppm | ASTM D5185m | | 2 | | |
| | Magnesium | ppm | ASTM D5185m | 145 | 120 | | |
| | Calcium | ppm | ASTM D5185m | 3570 | 3390 | | |
| | Phosphorus | ppm | ASTM D5185m | 1290 | 1084 | | |
| | Zinc | ppm | ASTM D5185m | 1640 | 1278 | | |
| | Sulfur | ppm | ASTM D5185m | | 3456 | | |
| | | - | | | | | |


Visc @ 40°C


cSt


ASTM D445 57.0

Contact/Location: DAVID ZIEG - JAMASH

50.4







Contact/Location: DAVID ZIEG - JAMASH Page 2 of 2