

WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL



Store 9 - Marietta JOHN DEERE 350P 1FF350PAHPF000901

Left Propel Gearbox

JOHN DEERE GL-5 80W90 (2 GAL)


RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0049835		
	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		685		
	Oil Age	hrs	Client Info		685		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Changed		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184	1050	90		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		645		
	Chromium	ppm	ASTM D5185m		8		
	Nickel	ppm	ASTM D5185m	>10	1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		2		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		1		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m		24		
	Potassium	ppm	ASTM D5185m	>20	1		
	Water	le le	WC Method		NEG		
	Silt	scalar	*Visual	NONE	LIGHT		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		63		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<1		
	Manganese	ppm	ASTM D5185m		11		
	Magnesium	ppm	ASTM D5185m		<1		
	Calcium	ppm	ASTM D5185m		9		
	Phosphorus	ppm	ASTM D5185m		505		
	Zinc	ppm	ASTM D5185m		13		
	Sulfur	ppm	ASTM D5185m		13755		
	Vian @ 10°C	oC+	ACTM D445		100		


Visc @ 40°C cSt


ASTM D445

Submitted By: JOHN MARTIN

182







Submitted By: JOHN MARTIN Page 2 of 2