



|                 |               |
|-----------------|---------------|
| WEAR            | <b>NORMAL</b> |
| CONTAMINATION   | <b>NORMAL</b> |
| FLUID CONDITION | <b>NORMAL</b> |

Area

**[05W48057]**

Machine Id

**JOHN DEERE 750L 1T0750LXCNF430917**

Component

**Right Inner Final Drive**

Fluid

**JOHN DEERE HY-GARD HYD/TRANS (12 QTS)**

### RECOMMENDATION

Resample at the next service interval to monitor.

| Test           | UOM | Method      | Limit/Abn | Current            | History1    | History2    |
|----------------|-----|-------------|-----------|--------------------|-------------|-------------|
| Sample Number  |     | Client Info |           | <b>JR0226419</b>   | JR0210989   | JR0196116   |
| Sample Date    |     | Client Info |           | <b>12 Jul 2024</b> | 08 Apr 2024 | 08 Dec 2023 |
| Machine Age    | hrs | Client Info |           | <b>2962</b>        | 2480        | 1970        |
| Oil Age        | hrs | Client Info |           | <b>992</b>         | 510         | 1492        |
| Filter Age     | hrs | Client Info |           | <b>0</b>           | 0           | 0           |
| Oil Changed    |     | Client Info |           | <b>Changed</b>     | Not Chngd   | Changed     |
| Filter Changed |     | Client Info |           | <b>N/A</b>         | N/A         | None        |
| Sample Status  |     |             |           | <b>NORMAL</b>      | NORMAL      | NORMAL      |

### WEAR

All component wear rates are normal.

|              |        |             |       |              |      |      |
|--------------|--------|-------------|-------|--------------|------|------|
| PQ           |        | ASTM D8184  | >1250 | <b>16</b>    | 14   | 16   |
| Iron         | ppm    | ASTM D5185m | >750  | <b>8</b>     | 5    | 16   |
| Chromium     | ppm    | ASTM D5185m | >9    | <b>&lt;1</b> | 0    | 0    |
| Nickel       | ppm    | ASTM D5185m | >10   | <b>&lt;1</b> | 0    | 0    |
| Titanium     | ppm    | ASTM D5185m |       | <b>&lt;1</b> | <1   | 0    |
| Silver       | ppm    | ASTM D5185m |       | <b>0</b>     | 0    | 0    |
| Aluminum     | ppm    | ASTM D5185m | >40   | <b>2</b>     | 2    | 1    |
| Lead         | ppm    | ASTM D5185m | >15   | <b>&lt;1</b> | 0    | <1   |
| Copper       | ppm    | ASTM D5185m | >40   | <b>&lt;1</b> | 1    | 0    |
| Tin          | ppm    | ASTM D5185m | >10   | <b>&lt;1</b> | 0    | 0    |
| Vanadium     | ppm    | ASTM D5185m |       | <b>0</b>     | 0    | 0    |
| White Metal  | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE | NONE |
| Yellow Metal | scalar | *Visual     | NONE  | <b>NONE</b>  | NONE | NONE |

### CONTAMINATION







There is no indication of any contamination in the oil.

|                  |        |             |        |              |       |       |
|------------------|--------|-------------|--------|--------------|-------|-------|
| Silicon          | ppm    | ASTM D5185m | >75    | <b>6</b>     | 3     | 6     |
| Potassium        | ppm    | ASTM D5185m | >20    | <b>1</b>     | 2     | 2     |
| Water            |        | WC Method   | >0.075 | <b>NEG</b>   | NEG   | NEG   |
| Silt             | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Debris           | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Sand/Dirt        | scalar | *Visual     | NONE   | <b>NONE</b>  | NONE  | NONE  |
| Appearance       | scalar | *Visual     | NORML  | <b>NORML</b> | NORML | NORML |
| Odor             | scalar | *Visual     | NORML  | <b>NORML</b> | NORML | NORML |
| Emulsified Water | scalar | *Visual     | >0.075 | <b>NEG</b>   | NEG   | NEG   |

### FLUID CONDITION

The condition of the oil is acceptable for the time in service.

|             |     |             |      |              |      |      |
|-------------|-----|-------------|------|--------------|------|------|
| Sodium      | ppm | ASTM D5185m | >51  | <b>0</b>     | 0    | 0    |
| Boron       | ppm | ASTM D5185m | 6    | <b>16</b>    | 15   | 6    |
| Barium      | ppm | ASTM D5185m | 0    | <b>0</b>     | 0    | 0    |
| Molybdenum  | ppm | ASTM D5185m | 0    | <b>13</b>    | 11   | 5    |
| Manganese   | ppm | ASTM D5185m |      | <b>&lt;1</b> | 0    | 0    |
| Magnesium   | ppm | ASTM D5185m | 145  | <b>140</b>   | 135  | 127  |
| Calcium     | ppm | ASTM D5185m | 3570 | <b>3497</b>  | 3570 | 3782 |
| Phosphorus  | ppm | ASTM D5185m | 1290 | <b>1092</b>  | 1218 | 1125 |
| Zinc        | ppm | ASTM D5185m | 1640 | <b>1282</b>  | 1291 | 1393 |
| Sulfur      | ppm | ASTM D5185m |      | <b>3451</b>  | 4228 | 4569 |
| Visc @ 40°C | cSt | ASTM D445   | 57.0 | <b>51.1</b>  | 58.5 | 52.5 |



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : JR0226419 **Received** : 15 Jul 2024  
**Lab Number** : 06236394 **Tested** : 16 Jul 2024  
**Unique Number** : 11125228 **Diagnosed** : 16 Jul 2024 - Wes Davis  
**Test Package** : CONST ( Additional Tests: PQ )

**JRE - MANASSAS PARK**  
 9107 OWENS DRIVE  
 MANASSAS PARK, VA  
 US 20111  
 Contact: TECHNICIAN ACCOUNT  
 catherine.anastasio@wearcheck.com  
 T:  
 F: (703)631-4715

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)