

WEAR CONTAMINATION **FLUID CONDITION**

ABNORMAL NORMAL NORMAL

Store 4 - Fairmont [RO# 152869]


PRINOTH T12 935300157

Left Final Drive

GEAR OIL SAE 80W90 (2 GAL)

GEAR OIL SAE 80W90 (2 GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
No corrective action is recommended at this time. Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0050976	LEC0018171	
	Sample Date		Client Info		06 Jul 2024	06 Jan 2021	
	Machine Age	hrs	Client Info		2737	1411	
	Oil Age	hrs	Client Info		1326	1411	
	Filter Age	hrs	Client Info		0	0	
	Oil Changed		Client Info		Changed	Changed	
	Filter Changed		Client Info		N/A	Not Changd	
	Sample Status				ABNORMAL	ABNORMAL	
WEAR	PQ		ASTM D8184		159	758	
Bearing and/or bushing wear is indicated.	Iron	ppm	ASTM D5185m	>500	495	<u></u> 881	
	Chromium	ppm	ASTM D5185m	>10	7	12	
	Nickel	ppm	ASTM D5185m	>10	<1	<1	
	Titanium	ppm	ASTM D5185m		2	10	
	Silver	ppm	ASTM D5185m		0	<1	
	Aluminum	ppm	ASTM D5185m	>25	16	12	
	Lead	ppm	ASTM D5185m	>25	^ 29	<u> </u>	
	Copper	ppm	ASTM D5185m	>50	170	81	
	Tin	ppm	ASTM D5185m	>10	4	3	
	Vanadium	ppm	ASTM D5185m		0	<1	
	White Metal	scalar	*Visual	NONE	NONE	MODER	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
CONTAMINATION	Silicon	ppm	ASTM D5185m		67	36	
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		6	3	
	Water		WC Method	>0.2	NEG	NEG	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
	Appearance	scalar	*Visual	NORML	NORML	NORML	
	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	<1	14	
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	1	17	
	Barium	ppm	ASTM D5185m	200	0	36	
	Molybdenum	ppm	ASTM D5185m	12	1	2	
	Manganese	ppm	ASTM D5185m		4	7	
	Magnesium	ppm	ASTM D5185m	12	9	6	
	Calcium	ppm	ASTM D5185m	150	78	11	
	Phosphorus	ppm	ASTM D5185m	1650	295	410	
	Zinc	ppm	ASTM D5185m	125	37	32	
	Sulfur	ppm	ASTM D5185m	22500	16457	5396	
	Visc @ 40°C	cSt	ASTM D445	143	131	206	

Submitted By: APRIL TREADWAY







Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No.

: LEC0050976 Lab Number : 06236397 Unique Number : 11125231

Received **Tested** Diagnosed

: 17 Jul 2024 - Sean Felton Test Package : CONST (Additional Tests: PQ) To discuss this sample report, contact Customer Service at 1-800-237-1369.

: 15 Jul 2024

: 16 Jul 2024

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765 Contact: LEANNE KENDALL

KendalLeanne@lec1.com

T: F: (740)373-5570