



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
429123
Component
1 Differential
Fluid
GEAR OIL SAE 80W90 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0128748	GFL0112128	GFL0085415
Sample Date		Client Info		10 Jul 2024	03 May 2024	06 Jul 2023
Machine Age	mls	Client Info		289187	270516	232272
Oil Age	mls	Client Info		289187	28656	232271
Filter Age	mls	Client Info		289187	0	0
Oil Changed		Client Info		N/A	Changed	Changed
Filter Changed		Client Info		N/A	Changed	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>1200	96	69	551
Chromium	ppm	ASTM D5185m	>8	<1	<1	4
Nickel	ppm	ASTM D5185m	>20	4	7	26
Titanium	ppm	ASTM D5185m	>4	0	<1	<1
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	30	27	53
Lead	ppm	ASTM D5185m	>25	0	<1	0
Copper	ppm	ASTM D5185m	>50	0	2	0
Tin	ppm	ASTM D5185m	>5	0	1	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION





There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>230	53	97	159
Potassium	ppm	ASTM D5185m	>20	2	2	2
Water		WC Method	>.2	NEG	NEG	NEG
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m	>170	3	0	4
Boron	ppm	ASTM D5185m	400	36	46	111
Barium	ppm	ASTM D5185m	200	0	0	0
Molybdenum	ppm	ASTM D5185m	12	0	2	<1
Manganese	ppm	ASTM D5185m		<1	2	7
Magnesium	ppm	ASTM D5185m	12	0	3	12
Calcium	ppm	ASTM D5185m	150	17	158	21
Phosphorus	ppm	ASTM D5185m	1650	403	571	1038
Zinc	ppm	ASTM D5185m	125	24	240	20
Sulfur	ppm	ASTM D5185m	22500	14050	8818	23414
Visc @ 40°C	cSt	ASTM D445	143	44.1	58.3	133



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : GFL0128748
Lab Number : 06236568
Unique Number : 11125402
Test Package : FLEET

Received : 15 Jul 2024
Tested : 16 Jul 2024
Diagnosed : 17 Jul 2024 - Sean Felton

GFL Environmental - 983 - Sugar Land Hauling
 16011 West Belfort Street
 Sugar Land, TX
 US 77498
 Contact: TECHNICIAN ACCOUNT
 wcgfldemo@gmail.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: