WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL


Area


Ascendum Machinery VOLVO A30G 753667 Component


Drop Box


VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

VOLVO SUPER GEAR OIL 75W-80-GO102 (GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0008366		
	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		517		
	Oil Age	hrs	Client Info		517		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m	>500	89		
	Chromium	ppm	ASTM D5185m	>20	2		
All component wear rates are normal.	Nickel	ppm	ASTM D5185m		<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>30	<1		
	Lead	ppm	ASTM D5185m	>30	0		
	Copper	ppm	ASTM D5185m	>30	9		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Ciliana		ACTM DE10E	F0			
	Silicon	ppm	ASTM D5185m		6		
There is no indication of any contamination in the oil.	Potassium Water	ppm	ASTM D5185m		3		
	Silt	cooler	WC Method *Visual	>0.2 NONE	NEG MODER		
	Debris	scalar scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water		*Visual	>0.2	NEG		
ELUID CONDITION							
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		258		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		2		
	Magagium	ppm	ASTM D5185m		8		
	Magnesium	ppm	ASTM D5185m		792		
	Calcium	ppm	ASTM D5185m		782		
	Phosphorus Zinc	ppm	ASTM D5185m ASTM D5185m		1302		
	Sulfur	ppm	ASTM D5185m		311 20675		
	Visc @ 40°C	ppm cSt	ASTM D5185m		82.7		
	VISC @ 40°C	COL	49 LINI D442	1	02./		











Certificate L2367

Laboratory Sample No.

: ASC0008366 Lab Number : 06236607 Unique Number : 11125441 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024

Tested : 16 Jul 2024 Diagnosed : 17 Jul 2024 - Sean Felton

WM WARR & SON 3800 SMITH FARM RD

MATTHEWS, NC US 28104

Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: