





## Ascendum Machinery VOLVO A30G 753667 Front Left Final Drive

VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

		·					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		ASC0008370		
	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		517		
	Oil Age	hrs	Client Info		517		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR				000	440		
WEAR	Iron	ppm	ASTM D5185m		110		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		3		
	Nickel	ppm	ASTM D5185m	>10	<1		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m	00	0		
	Aluminum	ppm	ASTM D5185m		0		
	Lead	ppm	ASTM D5185m ASTM D5185m		0		
	Copper	ppm		>150	9		
	Tin	ppm	ASTM D5185m	>20	0		
	Vanadium	ppm	ASTM D5185m	NONE	0		
	White Metal	scalar	*Visual	NONE	LIGHT		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>50	5		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	5		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	MODER		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		3		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		259		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		5		
	Manganese	ppm	ASTM D5185m		8		
	Magnesium	ppm	ASTM D5185m		0		
	Calcium	ppm	ASTM D5185m		606		
	Phosphorus	ppm	ASTM D5185m		1327		
	Zinc	ppm	ASTM D5185m		249		
	Sulfur	ppm	ASTM D5185m		21875		
	Visc @ 40°C	cSt	ASTM D445		90.7		

Submitted By: KARRINGTON RENDLEMAN







Sample No. : ASC0008370 Received 3800 SMITH FARM RD : 15 Jul 2024 Lab Number : 06236608 Tested MATTHEWS, NC : 16 Jul 2024 Unique Number : 11125442 Diagnosed : 17 Jul 2024 - Sean Felton US 28104 Test Package : CONST Contact: SERVICE MANAGER Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F:

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Laboratory

Submitted By: KARRINGTON RENDLEMAN Page 2 of 2

WM WARR & SON