

**WEAR** CONTAMINATION **FLUID CONDITION**  **ABNORMAL NORMAL ATTENTION** 



## KOMATSU HD465-5 60 (S/N 4963)

Silver

Lead

Tin

Copper

Vanadium

White Metal

Yellow Metal

Aluminum

**Left Final Drive** 

**SAE 30W (--- GAL)** 

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		LP0001354		
Sample Date		Client Info		01 Jul 2024		
Machine Age	hrs	Client Info		31680		
Oil Age	hrs	Client Info		1412		
Filter Age	hrs	Client Info		1412		
Oil Changed		Client Info		Changed		
Filter Changed		Client Info		Changed		
Sample Status				ABNORMAL		
Iron	ppm	ASTM D5185m	>500	19		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		

0

3

0

73

0

0

NONE

NONE

ASTM D5185m

ASTM D5185m >25

ASTM D5185m >25

ASTM D5185m >50

ASTM D5185m >10

ASTM D5185m

\*Visual

\*Visual

ppm

ppm

ppm

ppm

ppm

ppm

scalar

scalar

## **WEAR**

The copper level is abnormal. All other component wear rates are normal.

CONTAMINATION
---------------

There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>75	5	 
Potassium	ppm	ASTM D5185m	>20	1	 
Water	1-1-	WC Method	>0.2	NEG	 
Silt	scalar	*Visual	NONE	NONE	 
Debris	scalar	*Visual	NONE	NONE	 
Sand/Dirt	scalar	*Visual	NONE	NONE	 
Appearance	scalar	*Visual	NORML	NORML	 
Odor	scalar	*Visual	NORML	NORML	 
Emulsified Water	scalar	*Visual	>0.2	NEG	 
Sodium	ppm	ASTM D5185m		0	 

NONE

NONE

## FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Odor	scalar	*Visual	NORML	NORML		
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG		
Sodium	ppm	ASTM D5185m		0		
Boron	ppm	ASTM D5185m		28		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		9		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		317		
Calcium	ppm	ASTM D5185m		2243		
Phosphorus	ppm	ASTM D5185m		1115		
Zinc	ppm	ASTM D5185m		1237		
Sulfur	ppm	ASTM D5185m		<b>3733</b>		
Acid Number (AN)	mg KOH/g	ASTM D8045		1.39		
Visc @ 40°C	cSt	ASTM D445	95.0	51.9		
		Contac	ct/Location	on: PAUL BE	CKMAN - SI	MLWALNO





Certificate L2367

Laboratory

Sample No.

: LP0001354 Lab Number : 06237013 Unique Number : 11125847 Test Package : MOB 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Jul 2024 **Tested** : 17 Jul 2024 Diagnosed

: 17 Jul 2024 - Sean Felton

US 02081 Contact: PAUL BECKMAN pbeckman@smlorusso.com T: (508)668-2603

S.M. LORUSSO & SONS

221 NORFOLK ST.

WALPOLE, MA

F: (508)660-0232

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)