



TRAAP

Texas Refinery Advanced Analysis Program

OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
MACK 2013 MACK
 Component
Diesel Engine
 Fluid
TRC PRO-SPEC III SYNTHETIC BLEND 15W40 (8 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		TR06237086	---	---
Sample Date		Client Info		01 Jul 2024	---	---
Machine Age	mls	Client Info		577308	---	---
Oil Age	mls	Client Info		4380	---	---
Filter Age	mls	Client Info		4380	---	---
Oil Changed		Client Info		Changed	---	---
Filter Changed		Client Info		Changed	---	---
Sample Status				NORMAL	---	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>120	106	---	---
Chromium	ppm	ASTM D5185m	>20	3	---	---
Nickel	ppm	ASTM D5185m	>5	4	---	---
Titanium	ppm	ASTM D5185m	>2	0	---	---
Silver	ppm	ASTM D5185m	>2	0	---	---
Aluminum	ppm	ASTM D5185m	>20	12	---	---
Lead	ppm	ASTM D5185m	>40	3	---	---
Copper	ppm	ASTM D5185m	>330	5	---	---
Tin	ppm	ASTM D5185m	>15	<1	---	---
Vanadium	ppm	ASTM D5185m		0	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

CONTAMINATION












There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	11	---	---
Potassium	ppm	ASTM D5185m	>20	5	---	---
Fuel		WC Method	>3.0	<1.0	---	---
Water		WC Method	>0.2	NEG	---	---
Glycol		WC Method		NEG	---	---
Soot %	%	*ASTM D7844	>4	0.4	---	---
Nitration	Abs/cm	*ASTM D7624	>20	18.3	---	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	30.2	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		7	---	---
Boron	ppm	ASTM D5185m		20	---	---
Barium	ppm	ASTM D5185m		0	---	---
Molybdenum	ppm	ASTM D5185m		45	---	---
Manganese	ppm	ASTM D5185m		1	---	---
Magnesium	ppm	ASTM D5185m		494	---	---
Calcium	ppm	ASTM D5185m		1789	---	---
Phosphorus	ppm	ASTM D5185m		750	---	---
Zinc	ppm	ASTM D5185m		957	---	---
Sulfur	ppm	ASTM D5185m		2095	---	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	41.0	---	---
Base Number (BN)	mg KOH/g	ASTM D2896		4.32	---	---
Visc @ 100°C	cSt	ASTM D445	15.5	12.7	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : TR06237086
 Lab Number : 06237086
 Unique Number : 11125920
 Test Package : MOB 2
 Received : 15 Jul 2024
 Tested : 18 Jul 2024
 Diagnosed : 18 Jul 2024 - Jonathan Hester

NOLL CONSTRUCTION
 BOX 152
 GOLVA, ND
 US 58632
 Contact: KELLY ZIETTLLOW

To discuss this sample report, contact Customer Service at 1-800-827-0711.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: (701)872-3823