**WEAR CONTAMINATION FLUID CONDITION**  **NORMAL NORMAL NORMAL** 

PETER HANSEN [6762] **VOLVO PENTA IPS-F 3940016643** 

**Port IPS** 

{not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		VPA055706		
	Sample Date		Client Info		09 Jul 2024		
	Machine Age	hrs	Client Info		511		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Not Changd		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		20		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>275	44		
	Chromium	ppm	ASTM D5185m	>4	<1		
	Nickel	ppm	ASTM D5185m	>4	<1		
	Titanium	ppm	ASTM D5185m	>3	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>10	3		
	Lead	ppm	ASTM D5185m	>4	0		
	Copper	ppm	ASTM D5185m		5		
	Tin	ppm	ASTM D5185m	>3	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION  There is no indication of any contamination in the oil.	Silicon	ppm	ASTM D5185m	>35	7		
	Potassium	ppm	ASTM D5185m	>20	1		
	Water		WC Method	>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		12		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		332		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		3		
	Calcium	ppm	ASTM D5185m		0		
	Phosphorus	ppm	ASTM D5185m		1358		
	Zinc	ppm	ASTM D5185m		13		
	Sulfur	ppm	ASTM D5185m		23653		
Papert Id: \/P750000 [WI ICCAD] 06997007 (Caparated: 07/17/2094 15:49:40) Pays 1	Visc @ 40°C	cSt	ASTM D445	. "	105		 VD750000







Laboratory Sample No.

Lab Number : 06237097 Unique Number : 11125931 Test Package: MOB 1 (Additional Tests: PQ)

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : VPA055706

Received **Tested** Diagnosed

: 15 Jul 2024 : 17 Jul 2024

: 17 Jul 2024 - Don Baldridge

US 98225 Contact: TRAVIS THOMAS

1325 ROEDER AVE SUITE 103

ttdiesel@yahoo.com T: (360)739-9525

**Northwest Diesel Power** 

BELLINGHAM, WA

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: