



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area

WILLARD HAMMOND

Machine Id

[WILLARD HAMMOND] 007 587215-7

Component

Port Genset

Fluid

CHEVRON DELO 400 MULTIGRADE 15W40 (4 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0070945	MW0072270	MW0070928
Sample Date		Client Info		01 Jul 2024	01 Jun 2024	01 May 2024
Machine Age	hrs	Client Info		40380	39994	39898
Oil Age	hrs	Client Info		384	0	300
Filter Age	hrs	Client Info		384	0	300
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Filter Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	4	3	4
Chromium	ppm	ASTM D5185m	>4	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m	>5	0	<1	<1
Aluminum	ppm	ASTM D5185m	>12	3	4	3
Lead	ppm	ASTM D5185m	>17	0	0	<1
Copper	ppm	ASTM D5185m	>70	0	<1	0
Tin	ppm	ASTM D5185m	>15	0	0	0
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	7	5
Potassium	ppm	ASTM D5185m	>20	0	2	<1
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	7.1	4.9	6.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.3	21.5	22.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		1	2	0
Boron	ppm	ASTM D5185m	151	307	387	361
Barium	ppm	ASTM D5185m	0.4	0	<1	0
Molybdenum	ppm	ASTM D5185m	250	121	119	128
Manganese	ppm	ASTM D5185m		5	<1	2
Magnesium	ppm	ASTM D5185m	0	608	589	681
Calcium	ppm	ASTM D5185m	2046	1679	1559	1925
Phosphorus	ppm	ASTM D5185m	1043	832	798	883
Zinc	ppm	ASTM D5185m	943	963	900	1085
Sulfur	ppm	ASTM D5185m	5012	3300	2567	3598
Oxidation	Abs/.1mm	*ASTM D7414	>25	17.0	14.7	16.4
Base Number (BN)	mg KOH/g	ASTM D2896	12.5	8.2	9.3	8.5
Visc @ 100°C	cSt	ASTM D445	14.4	13.1	13.7	13.1



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0070945
Lab Number : 06237306
Unique Number : 11126140
Test Package : MAR 2

Received : 15 Jul 2024
Tested : 17 Jul 2024
Diagnosed : 17 Jul 2024 - Wes Davis

INGRAM BARGE
 900 S 3RD ST
 PADUCAH, KY
 US 42003
 Contact: CHARLES COPELAND
 charles.copeland@ingrambarga.com
 T: (270)415-4467
 F: (615)695-3697

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)