

## WEAR NORMAL CONTAMINATION NORMAL FLUID CONDITION NORMAL

Machine Id

24G1104 CYLL-005 Component New (Unused) Oil

{not provided} (--- GAL)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
This is a baseline read-out on the submitted sample.	Sample Number		Client Info		HPL0005271		
	Sample Date		Client Info		12 Jul 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	ppm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m		<1		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		0		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		2		
	Potassium	ppm	ASTM D5185m	>20	2		
	Water	pp	WC Method	/ 10	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
	Boron	ppm	ASTM D5185m		0		
	Barium	ppm	ASTM D5185m		۰ <1		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		322		
	Calcium	ppm	ASTM D5185m		201		
	Phosphorus	ppm	ASTM D5185m		2		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		21130		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.18		
	Visc @ 40°C	cSt	ASTM D445		148.6		
	Visc @ 100°C	cSt	ASTM D445		17.43		

Viscosity Index (VI) Scale ASTM D2270

128



