

WEAR CONTAMINATION **FLUID CONDITION**


NORMAL NORMAL NORMAL

Machine Id

24G1103 ATF-520

New (Unused) Oil

RECOMMENDATION This is a baseline read-out on the submitted sample.	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		HPL0005649		
	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		0		
	Oil Age	hrs	Client Info		0		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	Iron	nnm	ASTM D5185m		0		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm					
	Titanium	ppm	ASTM D5185m ASTM D5185m		0		
	Silver	ppm	ASTM D5185m		0		
		ppm					
	Aluminum	ppm	ASTM D5185m ASTM D5185m		<1 0		
	Lead	ppm			0		
	Copper Tin	ppm	ASTM D5185m ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	ppm	*Visual	NONE	NONE		
	Yellow Metal	scalar		NONE	NONE		
	Tollow Motal		· · · · · · · · ·				
CONTAMINATION	Silicon	ppm	ASTM D5185m		1		
	Potassium	ppm	ASTM D5185m	>20	<1		
	Water		WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual		NEG		
FLUID CONDITION	O = eli:		ACTM DE10E		•		
PLOID CONDITION	Sodium	ppm	ASTM D5185m		3		
	Boron	ppm	ASTM D5185m		120		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		0		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		7		
	Calcium	ppm	ASTM D5185m		402		
	Phosphorus	ppm	ASTM D5185m		314		
	Zinc	ppm	ASTM D5185m		0		
	Sulfur	ppm	ASTM D5185m		2758		
	, ,	mg KOH/g	ASTM D8045		1.17		
	Visc @ 40°C	cSt	ASTM D445		37.54		
	Visc @ 100°C	cSt	ASTM D445		7.48		
	Viscosity Index (VI)		ASTM D2270		171		







Laboratory Sample No.

: HPL0005649 Lab Number : 06237449

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Tested Unique Number : 11126283 Diagnosed

Received : 15 Jul 2024 : 18 Jul 2024

: 18 Jul 2024 - Jonathan Hester

HIGH PERFORMANCE LUBRICANTS LLC 500 S SPRUCE ST

MANTENO, IL US 60950 Contact: DAVID WARD

T: (815)468-3535

Test Package : MOB 2 (Additional Tests: FT-IR, ICP-NewOil, KV100, PrtCount, VI) Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369. sampledata@hplubricants.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: