



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
SENNEBOGEN 835M 835.0.3072

Component
Diesel Engine

Fluid
{not provided} (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0221816	JR0210006	JR0210313
Sample Date		Client Info		12 Jul 2024	13 May 2024	14 Mar 2024
Machine Age	hrs	Client Info		1524	1016	513
Oil Age	hrs	Client Info		1016	513	0
Filter Age	hrs	Client Info		1016	513	0
Oil Changed		Client Info		Changed	Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	10	14	30
Chromium	ppm	ASTM D5185m	>20	0	<1	1
Nickel	ppm	ASTM D5185m	>4	0	0	<1
Titanium	ppm	ASTM D5185m		0	<1	3
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	5	8	10
Lead	ppm	ASTM D5185m	>40	0	0	<1
Copper	ppm	ASTM D5185m	>330	1	3	15
Tin	ppm	ASTM D5185m	>15	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	8	17
Potassium	ppm	ASTM D5185m	>20	10	13	40
Fuel		WC Method	>5	<1.0	<1.0	1.7
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.6	0.2
Nitration	Abs/cm	*ASTM D7624	>20	9.5	9.7	9.8
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.8	24.1	20.5
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		6	5	4
Boron	ppm	ASTM D5185m		167	239	58
Barium	ppm	ASTM D5185m		<1	<1	6
Molybdenum	ppm	ASTM D5185m		247	254	68
Manganese	ppm	ASTM D5185m		<1	1	6
Magnesium	ppm	ASTM D5185m		832	871	376
Calcium	ppm	ASTM D5185m		1484	1529	1785
Phosphorus	ppm	ASTM D5185m		885	926	982
Zinc	ppm	ASTM D5185m		1025	1113	1214
Sulfur	ppm	ASTM D5185m		3425	3603	3494
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.7	20.2	18.5
Base Number (BN)	mg KOH/g	ASTM D2896		8.4	7.9	6.5
Visc @ 100°C	cSt	ASTM D445		13.7	13.5	11.3



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0221816 **Received** : 16 Jul 2024
Lab Number : 06237570 **Tested** : 17 Jul 2024
Unique Number : 11126404 **Diagnosed** : 17 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

JRE - STEPHENSON
 245 YARDMASTER COURT
 STEPHENSON, VA
 US 22656-1761
 Contact: PHIL DAUGHERTY
 pdaugherty@jamesriverequipment.com
 T:
 F: (540)869-0549