



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
10855
Component
Diesel Engine
Fluid
PETRO CANADA DURON SHP 15W40 (13 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		GFL0122160	GFL0118106	GFL0112376
Sample Date		Client Info		15 Jul 2024	13 May 2024	22 Feb 2024
Machine Age	hrs	Client Info		670	462	65
Oil Age	hrs	Client Info		605	397	535
Filter Age	hrs	Client Info		605	397	535
Oil Changed		Client Info		Changed	Not Changd	Changed
Filter Changed		Client Info		Changed	Not Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	38	18	1
Chromium	ppm	ASTM D5185m	>5	1	<1	0
Nickel	ppm	ASTM D5185m	>4	<1	0	0
Titanium	ppm	ASTM D5185m	>2	0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>15	5	2	<1
Lead	ppm	ASTM D5185m	>25	0	0	0
Copper	ppm	ASTM D5185m	>100	5	0	<1
Tin	ppm	ASTM D5185m	>4	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>25	15	8	5
Potassium	ppm	ASTM D5185m	>20	3	<1	0
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>6	1.1	0.6	0.2
Nitration	Abs/cm	*ASTM D7624	>20	9.1	6.8	4.5
Sulfation	Abs/.1mm	*ASTM D7415	>30	19.7	17.7	16.8
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		37	24	6
Boron	ppm	ASTM D5185m	0	7	12	19
Barium	ppm	ASTM D5185m	0	0	1	0
Molybdenum	ppm	ASTM D5185m	60	64	60	59
Manganese	ppm	ASTM D5185m	0	<1	<1	<1
Magnesium	ppm	ASTM D5185m	1010	862	857	829
Calcium	ppm	ASTM D5185m	1070	1052	1048	990
Phosphorus	ppm	ASTM D5185m	1150	864	1004	936
Zinc	ppm	ASTM D5185m	1270	1178	1182	1087
Sulfur	ppm	ASTM D5185m	2060	2511	3305	2802
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.1	12.4	11.9
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	7.5	8.2	8.7
Visc @ 100°C	cSt	ASTM D445	15.4	13.2	12.9	13.6


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : GFL0122160

Lab Number : 06237585

Unique Number : 11126419

Test Package : FLEET

Received : 16 Jul 2024

Tested : 17 Jul 2024

Diagnosed : 17 Jul 2024 - Wes Davis

GFL Environmental - 010 - Stockbridge

1280 Rum Creek Parkway

Stockbridge, GA

US 30281

Contact: JOSHUA TINKER

joshuatinker@gflenv.com

T:

F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)