



WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL ATTENTION


Area

## Store 4 - Fairmont [RO# 152802] JOHN DEERE 320D 1T0320DJEDG250547

**Hydraulic System** 

JOHN DEERE ENGINE OIL PLUS 50 II 15W40 (5 GAL)

JOHN DEERE ENGINE OIL PLU			<u> </u>				
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
	Sample Number		Client Info		LEC0051533		
Resample at the next service interval to monitor.	Sample Date		Client Info		11 Jul 2024		
	Machine Age	hrs	Client Info		2425		
	Oil Age	hrs	Client Info		1000		
	Filter Age	hrs	Client Info		500		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		Changed		
	Sample Status				ATTENTION		
WEAR	PQ		ASTM D8184	>50	15		
	Iron	ppm	ASTM D5185m	>71	5		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	, 0	0		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>11	2		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		2		
	Tin	ppm	ASTM D5185m		0		
	Vanadium	ppm	ASTM D5185m	70	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	nnm	ASTM D5185m	- 24	 E		
	Potassium	ppm			5 0		
The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.		ppm	ASTM D5185m		-		
	Water		WC Method		NEG		
	Particles >4µm		ASTM D7647		7849		
	Particles >6µm		ASTM D7647		99		
	Particles >14µm		ASTM D7647		3		
	Particles >21µm		ASTM D7647		1		
	Particles >38µm		ASTM D7647		0		
	Particles >71µm		ASTM D7647		0		
	Oil Cleanliness		ISO 4406 (c)		20/14/9		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar		NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual *Visual	NORML	NORML		
	Emulsified Water	scalar	visuai	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>21	1		
A 1 199 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1	Boron	ppm	ASTM D5185m		<b>83</b>		
Additive levels indicate the addition of a different brand, or type of oil.  Confirm oil type. The AN level is acceptable for this fluid.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		<b>81</b>		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m		<b>285</b>		
	Calcium	ppm	ASTM D5185m		<b>558</b>		
	Phosphorus	ppm	ASTM D5185m		<b>518</b>		
	Zinc	ppm	ASTM D5185m		<b>582</b>		
	Sulfur	ppm	ASTM D5185m		905		
	Acid Number (AN)	mg KOH/g	ASTM D8045		0.85		





Certificate L2367

Laboratory

Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0051533 Lab Number : 06237654

Unique Number : 11126488 Test Package : CONST ( Additional Tests: PQ )

Received **Tested** Diagnosed

: 16 Jul 2024 : 17 Jul 2024

: 18 Jul 2024 - Don Baldridge

KendalLeanne@lec1.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR.

Contact: LEANNE KENDALL

MARIETTA, OH

US 45750-9765

F: (740)373-5570

T: