



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Machine Id
JOHN DEERE 410E 1DW410EBCNF715190
Component
Hydraulic System
Fluid
JOHN DEERE HYDRAU (50 GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0221034	JR0214173	JR0201085
Sample Date		Client Info		12 Jul 2024	03 May 2024	05 Feb 2024
Machine Age	hrs	Client Info		5482	5001	4375
Oil Age	hrs	Client Info		4856	626	4375
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

PQ		ASTM D8184	>50	15	16	14
Iron	ppm	ASTM D5185m	>71	8	4	9
Chromium	ppm	ASTM D5185m	>11	3	2	4
Nickel	ppm	ASTM D5185m	>6	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>11	<1	<1	<1
Lead	ppm	ASTM D5185m	>13	0	0	0
Copper	ppm	ASTM D5185m	>21	<1	<1	2
Tin	ppm	ASTM D5185m	>5	0	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION











The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>24	3	2	2
Potassium	ppm	ASTM D5185m	>20	<1	3	2
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647	>80000	760	496	1256
Particles >6µm		ASTM D7647	>5000	198	109	229
Particles >14µm		ASTM D7647	>640	20	5	19
Particles >21µm		ASTM D7647	>160	4	1	4
Particles >38µm		ASTM D7647	>40	1	0	1
Particles >71µm		ASTM D7647	>10	1	0	0
Oil Cleanliness		ISO 4406 (c)	>23/19/16	17/15/11	16/14/10	17/15/11
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	3	2	3
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		4	4	0
Calcium	ppm	ASTM D5185m	87	94	99	73
Phosphorus	ppm	ASTM D5185m	727	710	690	662
Zinc	ppm	ASTM D5185m	900	854	880	872
Sulfur	ppm	ASTM D5185m	1500	1892	1925	1539
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.62	0.60	0.66
Visc @ 40°C	cSt	ASTM D445	65	58.0	59.0	56.5



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0221034 **Received** : 16 Jul 2024
Lab Number : 06237673 **Tested** : 17 Jul 2024
Unique Number : 11126507 **Diagnosed** : 17 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: PQ)

JRE - NEW BERN
 3816 MARTIN LUTHER KING BLVD
 NEW BERN, NC
 US 28562
 Contact: NEW BERN SHOP
 nick.etheridge@jamesriverequipment.com; canastasio@wearcheckusa.com

Certificate L2367
 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)