



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL



Area
PCS
Machine Id
JOHN DEERE 744J LD08 - PCS
Component
Hydraulic System
Fluid
STP HYDRO OIL ISO AW 46 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		KL0014723	KL0013794	KL0013055
Sample Date		Client Info		09 Jul 2024	10 Apr 2024	03 Oct 2023
Machine Age	hrs	Client Info		9772	9703	9326
Oil Age	hrs	Client Info		2563	2499	2122
Filter Age	hrs	Client Info		2563	2499	2122
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>71	12	15	26
Chromium	ppm	ASTM D5185m	>11	<1	<1	<1
Nickel	ppm	ASTM D5185m	>6	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>11	0	0	<1
Lead	ppm	ASTM D5185m	>13	0	0	0
Copper	ppm	ASTM D5185m	>21	<1	1	<1
Tin	ppm	ASTM D5185m	>5	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION










The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Silicon	ppm	ASTM D5185m	>24	2	3	3
Potassium	ppm	ASTM D5185m	>20	0	0	<1
Water		WC Method	>0.075	NEG	NEG	NEG
Particles >4µm		ASTM D7647		2750	6018	3704
Particles >6µm		ASTM D7647	>5000	499	651	558
Particles >14µm		ASTM D7647	>640	42	33	26
Particles >21µm		ASTM D7647	>160	8	15	12
Particles >38µm		ASTM D7647	>40	0	0	1
Particles >71µm		ASTM D7647	>10	0	0	0
Oil Cleanliness		ISO 4406 (c)	>19/16	16/13	17/12	16/12
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.075	NEG	NEG	NEG

FLUID CONDITION

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>21	<1	2	0
Boron	ppm	ASTM D5185m		0	4	8
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		4	<1	7
Calcium	ppm	ASTM D5185m		221	278	477
Phosphorus	ppm	ASTM D5185m		425	393	467
Zinc	ppm	ASTM D5185m		434	379	473
Sulfur	ppm	ASTM D5185m		1784	1724	2028
Acid Number (AN)	mg KOH/g	ASTM D8045		0.44	0.46	0.482
Visc @ 40°C	cSt	ASTM D445		43.2	43.9	44.0



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KL0014723
Lab Number : 06237720
Unique Number : 11126554
Test Package : MOB 2

Received : 16 Jul 2024
Tested : 17 Jul 2024
Diagnosed : 17 Jul 2024 - Wes Davis

PIKES PEAK PERFORMANCE PRODUCTS
 7888 BULLET RD
 PEYTON, CO
 US 80831

Contact: SCOTT RIGGS
 rriggs.pikespeakperformance@gmail.com
 T: (303)434-0126

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: