

WEAR CONTAMINATION FLUID CONDITION


ATTENTION ABNORMAL NORMAL

Store 9 - Marietta

JOHN DEERE 850L 1T0850LXCPF444596

Right Outer Final Drive

TOOMATAD ATION	_				(_)		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
We advise that you check all areas where dirt can enter the system. Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0049839		
	Sample Date		Client Info		15 Jul 2024		
	Machine Age	hrs	Client Info		1641		
	Oil Age	hrs	Client Info		1641		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				ABNORMAL		
VEAR	DO.		ACTM DO104	1050	004		
VEAR	PQ		ASTM D8184		391		
All component wear rates are normal.	Iron	ppm	ASTM D5185m		372		
	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m	>10	2		
	Titanium	ppm	ASTM D5185m		2		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	1 9		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon		ACTM DE10Em	. 75			
		ppm	ASTM D5185m ASTM D5185m		▲ 92 7		
Elemental levels of silicon (Si) and aluminum (Al) indicate aluminasilicate (coarse dirt) ingress.	Potassium	ppm			, NEG		
	Water	acalar		>0.075			
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m	>51	0		
	Boron	ppm	ASTM D5185m		23		
The condition of the oil is acceptable for the time in service.	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		18		
	Manganese		ASTM D5185m	J	2		
	-	ppm		1/15			
	Magnesium	ppm	ASTM D5185m		152		
	Calcium	ppm	ASTM D5185m	3570	3084		
	Phosphorus	ppm		1290	760		
	Zinc	ppm	ASTM D5185m	1640	1152		
	Sulfur	ppm	ASTM D5185m		3015		
	Visc @ 40°C	cSt	ASTM D445	57 O	60.6		





Certificate L2367

Laboratory

Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : LEC0049839 Lab Number : 06238143

Unique Number : 11126977

Received **Tested** Diagnosed

Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL

KendalLeanne@lec1.com

T: F: (740)373-5570

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: 16 Jul 2024

: 17 Jul 2024

: 18 Jul 2024 - Don Baldridge