

WEAR
CONTAMINATION
FLUID CONDITION

NORMAL NORMAL ATTENTION

Area


Store 9 - Marietta

JOHN DEERE 850L 1T0850LXCPF444596

Left Outer Final Drive

JOHN DEERE HY-GARD HYD/TRANS (4 GAL)

JOHN DEERE HY-GARD HYD/T	RANS (4 G/	AL)					
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		LEC0049838		
·	Sample Date		Client Info		15 Jul 2024		
	Machine Age	hrs	Client Info		1641		
	Oil Age	hrs	Client Info		1641		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				ATTENTION		
WEAR	PQ		ASTM D8184	>1250	110		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	167		
	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		1		
	Titanium	ppm	ASTM D5185m		1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	14		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	<1		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTANINATION							
CONTAMINATION	Silicon	ppm		>75	60		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		5		
	Water			>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.075	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	<1		
The oil viscosity is higher than normal. Confirm oil type.	Boron	ppm	ASTM D5185m	6	26		
	Barium	ppm	ASTM D5185m	0	0		
	Molybdenum	ppm	ASTM D5185m	0	20		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	145	174		
	Calcium	ppm	ASTM D5185m	3570	3474		
	Phosphorus	ppm	ASTM D5185m	1290	887		
	Zinc	ppm	ASTM D5185m	1640	1335		
	Sulfur	ppm	ASTM D5185m		3512		
	Visc @ 40°C	cSt	ASTM D445	57.0	106		
Papart Id. I ECMAPOU [MIJCCAP] 06000144 (Caparated: 07/10/0004 10:44:07) Pay: 1					L'illa mai		







Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No.

: LEC0049838

Lab Number : 06238144 Unique Number : 11126978

Diagnosed Test Package : CONST (Additional Tests: PQ)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received

Tested

: 16 Jul 2024

: 17 Jul 2024

: 18 Jul 2024 - Don Baldridge

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

LESLIE EQUIPMENT COMPANY

105 TENNIS CENTER DR. MARIETTA, OH US 45750-9765

Contact: LEANNE KENDALL

Submitted By: JOHN MARTIN

KendalLeanne@lec1.com T:

F: (740)373-5570 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)