



WEAR	NORMAL
CONTAMINATION	ABNORMAL
FLUID CONDITION	NORMAL

Machine Id
BELLEVUE
Component
Port Genset
Fluid
DIESEL ENGINE OIL SAE 15W40 (15 GAL)

RECOMMENDATION

The oil change at the time of sampling has been noted. We recommend an early resample to monitor this condition. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0070017	MW0069942	MW0056962
Sample Date		Client Info		11 Jul 2024	31 May 2024	19 Apr 2024
Machine Age	hrs	Client Info		16222	15743	0
Oil Age	hrs	Client Info		500	500	500
Filter Age	hrs	Client Info		500	500	0
Oil Changed		Client Info		Changed	Changed	N/A
Filter Changed		Client Info		Changed	Changed	N/A
Sample Status				ABNORMAL	SEVERE	ABNORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>50	4	5	7
Chromium	ppm	ASTM D5185m	>4	<1	<1	<1
Nickel	ppm	ASTM D5185m	>2	<1	0	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>5	<1	0	0
Aluminum	ppm	ASTM D5185m	>12	2	3	2
Lead	ppm	ASTM D5185m	>17	0	<1	0
Copper	ppm	ASTM D5185m	>70	<1	<1	<1
Tin	ppm	ASTM D5185m	>15	0	<1	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION









There is a moderate amount of fuel present in the oil. Tests confirm the presence of fuel in the oil.

Silicon	ppm	ASTM D5185m	>25	4	4	4
Potassium	ppm	ASTM D5185m	>20	2	2	21
Fuel	%	ASTM D3524	>4.0	7.1	9.9	6.7
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		0.1	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	10.3	11.5	11.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	20.0	20.3	21.2
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The oil is no longer serviceable due to the presence of contaminants.

Sodium	ppm	ASTM D5185m	>158	1	0	16
Boron	ppm	ASTM D5185m	250	10	23	57
Barium	ppm	ASTM D5185m	10	0	0	0
Molybdenum	ppm	ASTM D5185m	100	10	24	48
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	450	125	280	564
Calcium	ppm	ASTM D5185m	3000	1972	1751	1657
Phosphorus	ppm	ASTM D5185m	1150	843	979	944
Zinc	ppm	ASTM D5185m	1350	994	1033	1125
Sulfur	ppm	ASTM D5185m	4250	3033	3490	3675
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.8	20.3	22.4
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	6.4	6.1	7.5
Visc @ 100°C	cSt	ASTM D445	14.4	12.7	11.6	12.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513

Sample No. : MW0070017

Lab Number : 06238687

Unique Number : 11127521

Test Package : MAR 2 (Additional Tests: PercentFuel)

Received : 16 Jul 2024

Tested : 18 Jul 2024

Diagnosed : 18 Jul 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

C & B MARINE

50 E RIVERCENTER BLVD, SUITE 1180

COVINGTON, KY

US 41011

Contact: DAVID WESTRICH

dwestrich@carlislebray.com

T: (812)290-4063

F: (859)655-7504