WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Machine Id

## **JOHN DEERE 50P 1FF050PAKPH000671**

**Right Final Drive** 

GEAR OIL SAE 80W90 (--- GAL)

GEAR OIL SAE 80W90 ( GAL)					.,		
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) GEAR OIL SAE 80W90. Please confirm.	Sample Number		Client Info		JR0219635		
	Sample Date		Client Info		03 Jul 2024		
	Machine Age	hrs	Client Info		509		
	Oil Age	hrs	Client Info		509		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		27		
	Iron	ppm	ASTM D5185m	>500	82		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		2		
	Nickel	ppm	ASTM D5185m		- <1		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>25	3		
	Lead	ppm	ASTM D5185m		<1		
	Copper	ppm	ASTM D5185m		21		
	Tin	ppm	ASTM D5185m		<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		3		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m	>20	3		
	Water			>0.2	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>170	9		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	400	43		
The condition of the on is acceptable for the time in service.	Barium	ppm	ASTM D5185m	200	<1		
	Molybdenum	ppm	ASTM D5185m	12	2		
	Manganese	ppm	ASTM D5185m		2		
	Magnesium	ppm	ASTM D5185m	12	5		
	Calcium	ppm	ASTM D5185m	150	35		
	Phosphorus	ppm	ASTM D5185m	1650	532		
	Zinc	ppm	ASTM D5185m	125	20		
	Sulfur	ppm	ASTM D5185m	22500	21457		
	Visc @ 40°C	cSt	ASTM D445		130		
Report Id: JAMCHA [WUSCAR] 06239417 (Generated: 07/18/2024 14:00:51) Rev: 1			Subn	nitted Bv	: Mike Youn	a - CHARLO	TTE SHOP





Certificate L2367

Laboratory Sample No.

: JR0219635 Lab Number : 06239417

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received **Tested** Unique Number : 11128251 Diagnosed Test Package : CONST ( Additional Tests: PQ )

: 18 Jul 2024

9550 STATESVILLE ROAD : 17 Jul 2024 : 18 Jul 2024 - Wes Davis

Contact: CHARLOTTE SHOP myoung@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (704)597-0211 F: (704)596-6198

CHARLOTTE, NC

US 28269