WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Machine Id

## **JOHN DEERE 750L 1T0750LXARF466857**


**Right Final Drive** 

{not provided} (--- GAL)

not provided} ( GAL)							
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.	Sample Number		Client Info		JR0220098		
	Sample Date		Client Info		15 Jul 2024		
	Machine Age	hrs	Client Info		526		
	Oil Age	hrs	Client Info		526		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	PQ		ASTM D8184	>1250	9		
All component wear rates are normal.	Iron	ppm	ASTM D5185m	>750	<1		
	Chromium	ppm	ASTM D5185m		0		
	Nickel	ppm	ASTM D5185m	>10	0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		0		
	Aluminum	ppm	ASTM D5185m	>40	<1		
	Lead	ppm	ASTM D5185m	>15	0		
	Copper	ppm	ASTM D5185m	>40	0		
	Tin	ppm	ASTM D5185m	>10	0		
	Vanadium	ppm	ASTM D5185m		0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	0.11.		AOTA DELOE				
CONTAMINATION	Silicon	ppm	ASTM D5185m		4		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		0		
	Water		WC Method	>0.075	NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor Emulsified Water	scalar scalar	*Visual  *Visual	NORML >0.075	NORML NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m	>51	1		
The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m		6		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m		5		
	Manganese	ppm	ASTM D5185m		0		
	Magnesium	ppm	ASTM D5185m		119		
	Calcium	ppm	ASTM D5185m		3395		
	Phosphorus	ppm	ASTM D5185m		1000		
	Zinc	ppm	ASTM D5185m		1189		
	Sulfur	ppm	ASTM D5185m		3918		
	Visc @ 40°C	cSt	ASTM D445		57.9		

Report Id: CARCHAJR [WUSCAR] 06239440 (Generated: 07/21/2024 12:17:59) Rev: 1

Submitted By: Mike Young - CHARLOTTE SHOP





Laboratory Sample No.

Lab Number : 06239440 Unique Number : 11128274

: JR0220098

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed Test Package : CONST ( Additional Tests: PQ )

: 18 Jul 2024 : 19 Jul 2024 - Wes Davis

: 17 Jul 2024

**CARLTON'S BACKHOE** 9550 STATESVILLE ROAD CHARLOTTE, NC US 28269

Submitted By: Mike Young - CHARLOTTE SHOP

Contact: LEO

T: (704)547-0211

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: