WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL


Machine Id

7419069

Component Diesel Engine

51300 10W30 (--- QTS)

RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		IL0036862		
	Sample Date		Client Info		18 Apr 2024		
	Machine Age	mls	Client Info		7603		
	Oil Age	mls	Client Info		0		
	Filter Age	mls	Client Info		0		
	Oil Changed		Client Info		N/A		
	Filter Changed		Client Info		N/A		
	Sample Status				NORMAL		
VEAR	Iron	ppm	ASTM D5185m	>100	44		
	Chromium	ppm	ASTM D5185m		<1		
Metal levels are typical for a new component breaking in.	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m	7 7	0		
	Silver	ppm	ASTM D5185m	\3	<1		
	Aluminum	ppm	ASTM D5185m		7		
	Lead	ppm	ASTM D5185m		0		
	Copper	ppm	ASTM D5185m		16		
	Tin	ppm	ASTM D5185m		1		
	Vanadium	ppm	ASTM D5185m	710	0		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m		17		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		10		
	Fuel	%	ASTM D3524		<1.0		
	Water		WC Method	>0.2	NEG		
	Glycol	21	WC Method	0	NEG		
	Soot %	%	*ASTM D7844		0.6		
	Nitration	Abs/cm	*ASTM D7624	>20	12.5		
	Sulfation	Abs/.1mm	*ASTM D7415		23.4		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
LUID CONDITION	Sodium	ppm	ASTM D5185m		6		
	Boron	ppm	ASTM D5185m		69		
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.	Barium	ppm	ASTM D5185m		1		
	Molybdenum	ppm	ASTM D5185m		50		
	Manganese	ppm	ASTM D5185m		4		
	Magnesium	ppm	ASTM D5185m		726		
	Calcium	ppm	ASTM D5185m		1161		
	Phosphorus	ppm	ASTM D5185m		747		
	Zinc	ppm	ASTM D5185m		905		
	Sulfur	ppm	ASTM D5185m		2707		
	Oxidation	Abs/.1mm	*ASTM D7414	>25	22.6		
	Base Number (BN)		ASTM D2896		7.0		
	(2.11)	99	ASTM D445		12.1		







Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : IL0036862 Lab Number : 06239691

Unique Number : 11128525

Received **Tested**

: 17 Jul 2024 : 19 Jul 2024 Diagnosed

: 19 Jul 2024 - Sean Felton

Test Package : FLEET (Additional Tests: FuelDilution, PercentFuel)

IDEALEASE-NORCROSS 4571 NORTH BUFORD HWY NORCROSS, GA US 30071-2808 Contact: RICK MARKS

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (770)300-0614