



OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
Pillen Family Farms
 Machine Id
MILTK35
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER 15W40 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		SBP0006869	SBP0006797	SBP0005324
Sample Date		Client Info		02 Jul 2024	18 Apr 2024	05 Feb 2024
Machine Age	hrs	Client Info		350	350	350
Oil Age	hrs	Client Info		0	0	350
Filter Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Filter Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>80	6	8	11
Chromium	ppm	ASTM D5185m	>5	<1	0	1
Nickel	ppm	ASTM D5185m	>2	0	0	<1
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>30	4	5	8
Lead	ppm	ASTM D5185m	>30	0	<1	0
Copper	ppm	ASTM D5185m	>150	9	12	52
Tin	ppm	ASTM D5185m	>5	<1	1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>20	6	7	8
Potassium	ppm	ASTM D5185m	>20	3	2	5
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844	>3	0.2	0.2	0.2
Nitration	Abs/cm	*ASTM D7624	>20	6.9	6.6	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.8	18.6	18.9
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		2	2	3
Boron	ppm	ASTM D5185m	0	3	0	2
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	57	64	66
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	0	957	1084	1038
Calcium	ppm	ASTM D5185m		1094	1213	1130
Phosphorus	ppm	ASTM D5185m		1032	1138	1103
Zinc	ppm	ASTM D5185m		1276	1425	1362
Sulfur	ppm	ASTM D5185m		3434	3821	3101
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.5	14.4	15.4
Base Number (BN)	mg KOH/g	ASTM D2896	9.4	8.8	8.6	8.2
Visc @ 100°C	cSt	ASTM D445	14	13.9	13.7	13.4



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : SBP0006869
Lab Number : 06239756
Unique Number : 11128590
Test Package : FLEET

Received : 17 Jul 2024
Tested : 18 Jul 2024
Diagnosed : 19 Jul 2024 - Sean Felton

Pillen Family Farms - 722828
 26741 NE-91
 Humphrey, NE
 US 61357

Contact: Troy Runge
 troyfr@pillenfamilypills.com
 T: (308)390-6733

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: