
WEAR CONTAMINATION FLUID CONDITION

NORMAL NORMAL NORMAL

Shag 12 Component Diesel Engine

| RECOMMENDATION   | Test             | UOM      | Method      | Limit/Abn | Current     | History1    | History2   |
|--|------------------|----------|-------------|-----------|-------------|-------------|------------|
| Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample. | Sample Number    |          | Client Info |           | SBP0006861  | SBP0006874  | SBP000681  |
|  | Sample Date      |          | Client Info |           | 20 Jun 2024 | 07 May 2024 | 18 Mar 202 |
|  | Machine Age      | hrs      | Client Info |           | 350         | 350         | 350        |
|  | Oil Age          | hrs      | Client Info |           | 0           | 0           | 350        |
|  | Filter Age       | hrs      | Client Info |           | 0           | 0           | 0          |
|  | Oil Changed      |          | Client Info |           | Not Changd  | Not Changd  | Not Chang  |
|  | Filter Changed   |          | Client Info |           | N/A         | N/A         | N/A        |
|  | Sample Status    |          |             |           | NORMAL      | NORMAL      | NORMAI     |
| WEAR   | Iron             | ppm      | ASTM D5185m | >100      | 2           | 3           | 3          |
|  | Chromium         | ppm      | ASTM D5185m | >20       | 0           | 0           | 0          |
| Metal levels are typical for a new component breaking in.  | Nickel           | ppm      | ASTM D5185m |           | 0           | 0           | 0          |
|  | Titanium         | ppm      | ASTM D5185m |           | 0           | 0           | 0          |
|  | Silver           | ppm      | ASTM D5185m | >3        | 0           | <1          | 0          |
|  | Aluminum         | ppm      | ASTM D5185m | >20       | <1          | <1          | 2          |
|  | Lead             | ppm      | ASTM D5185m | >40       | 0           | <1          | 0          |
|  | Copper           | ppm      | ASTM D5185m | >330      | <1          | 0           | <1         |
|  | Tin              | ppm      | ASTM D5185m | >15       | 0           | 0           | 0          |
|  | Vanadium         | ppm      | ASTM D5185m |           | 0           | 0           | 0          |
|  | White Metal      | scalar   | *Visual     | NONE      | NONE        | NONE        | NON        |
|  | Yellow Metal     | scalar   | *Visual     | NONE      | NONE        | NONE        | NON        |
| CONTAMINATION  | Silicon          | ppm      | ASTM D5185m | >25       | 3           | 2           | 2          |
| OSITIAMINATION   | Potassium        | ppm      | ASTM D5185m |           | 1           | -<br><1     | 0          |
| There is no indication of any contamination in the oil.  | Fuel             | le le    | WC Method   |           | <1.0        | <1.0        | <1.0       |
|  | Water            |          | WC Method   |           | NEG         | NEG         | NEG        |
|  | Glycol           |          | WC Method   |           | NEG         | NEG         | NEG        |
|  | Soot %           | %        | *ASTM D7844 | >3        | 0.2         | 0.2         | 0.2        |
|  | Nitration        | Abs/cm   | *ASTM D7624 | >20       | 5.4         | 5.9         | 6.1        |
|  | Sulfation        | Abs/.1mm | *ASTM D7415 | >30       | 17.8        | 18.2        | 18.2       |
|  | Silt             | scalar   | *Visual     | NONE      | NONE        | NONE        | NON        |
|  | Debris           | scalar   | *Visual     | NONE      | NONE        | NONE        | NON        |
|  | Sand/Dirt        | scalar   | *Visual     | NONE      | NONE        | NONE        | NONI       |
|  | Appearance       | scalar   | *Visual     | NORML     | NORML       | NORML       | NORN       |
|  | Odor             | scalar   | *Visual     | NORML     | NORML       | NORML       | NORN       |
|  | Emulsified Water | scalar   | *Visual     | >0.2      | NEG         | NEG         | NEG        |
| LUID CONDITION   | Sodium           | ppm      | ASTM D5185m |           | 2           | 0           | 2          |
|  | Boron            | ppm      | ASTM D5185m |           | 3           | 0           | 1          |
| The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.  | Barium           | ppm      | ASTM D5185m |           | 0           | 0           | 0          |
|  | Molybdenum       | ppm      | ASTM D5185m |           | 56          | 58          | 54         |
|  | Manganese        | ppm      | ASTM D5185m |           | 0           | 0           | 0          |
|  | Magnesium        | ppm      | ASTM D5185m |           | 940         | 1034        | 958        |
|  | Calcium          | ppm      | ASTM D5185m |           | 1045        | 1183        | 1080       |
|  | Phosphorus       | ppm      | ASTM D5185m |           | 1036        | 1142        | 924        |
|  | Zinc             | ppm      | ASTM D5185m |           | 1247        | 1401        | 1216       |
|  | Sulfur           | ppm      | ASTM D5185m |           | 3630        | 4000        | 3530       |
|  | Oxidation        | Abs/.1mm | *ASTM D7414 | >25       | 13.5        | 13.9        | 14.2       |
|  | Base Number (BN) | mg KOH/g | ASTM D2896  |           | 9.2         | 9.1         | 8.9        |
|  | Visc @ 100°C     | cSt      | ASTM D445   |           | 14.2        | 14.2        | 13.4       |







Certificate L2367

Laboratory Sample No.

Lab Number : 06239770 Unique Number : 11128604 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : SBP0006861

To discuss this sample report, contact Customer Service at 1-800-237-1369.

**Tested** Diagnosed

Received

: 18 Jul 2024

: 18 Jul 2024 - Wes Davis

: 17 Jul 2024

Contact: Troy Runge troyfr@pillenfamilyfarms.com T: (308)390-6733

Pillen Family Farms - 722828

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: PILHUM [WUSCAR] 06239770 (Generated: 07/18/2024 15:37:15) Rev: 1

26741 NE-91

Humphrey, NE

US 61357

F: