



WEAR	<b>NORMAL</b>
CONTAMINATION	<b>NORMAL</b>
FLUID CONDITION	<b>NORMAL</b>

Machine Id  
**2716**  
 Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 15W40 (40 GAL)**

**RECOMMENDATION**

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		<b>GFL0127792</b>	GFL0098992	GFL0098932
Sample Date		Client Info		<b>09 Jul 2024</b>	10 Jun 2024	14 May 2024
Machine Age	hrs	Client Info		<b>14271</b>	14128	13964
Oil Age	hrs	Client Info		<b>8732</b>	8732	13964
Filter Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed		Client Info		<b>N/A</b>	N/A	N/A
Filter Changed		Client Info		<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

**WEAR**

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>165	<b>16</b>	14	8
Chromium	ppm	ASTM D5185m	>5	<b>&lt;1</b>	1	0
Nickel	ppm	ASTM D5185m	>4	<b>0</b>	<1	0
Titanium	ppm	ASTM D5185m	>2	<b>0</b>	<1	<1
Silver	ppm	ASTM D5185m	>2	<b>0</b>	<1	0
Aluminum	ppm	ASTM D5185m	>20	<b>2</b>	3	4
Lead	ppm	ASTM D5185m	>150	<b>0</b>	1	<1
Copper	ppm	ASTM D5185m	>90	<b>&lt;1</b>	1	<1
Tin	ppm	ASTM D5185m	>5	<b>&lt;1</b>	<1	<1
Vanadium	ppm	ASTM D5185m		<b>0</b>	<1	0
White Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE

**CONTAMINATION**

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>35	<b>4</b>	6	8
Potassium	ppm	ASTM D5185m	>20	<b>3</b>	3	3
Fuel		WC Method	>3.0	<b>&lt;1.0</b>	<1.0	<1.0
Water		WC Method	>0.2	<b>NEG</b>	NEG	NEG
Glycol		WC Method		<b>NEG</b>	NEG	NEG
Soot %	%	*ASTM D7844	>7.5	<b>0.4</b>	0.3	0.2
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.2</b>	7.8	6.4
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.7</b>	19.7	18.6
Silt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Debris	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	<b>NONE</b>	NONE	NONE
Appearance	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Odor	scalar	*Visual	NORML	<b>NORML</b>	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	<b>NEG</b>	NEG	NEG

**FLUID CONDITION**


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m		<b>4</b>	4	4
Boron	ppm	ASTM D5185m	0	<b>2</b>	<1	1
Barium	ppm	ASTM D5185m	0	<b>0</b>	1	0
Molybdenum	ppm	ASTM D5185m	60	<b>56</b>	58	53
Manganese	ppm	ASTM D5185m	0	<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m	1010	<b>929</b>	934	866
Calcium	ppm	ASTM D5185m	1070	<b>1083</b>	1078	984
Phosphorus	ppm	ASTM D5185m	1150	<b>1041</b>	1040	966
Zinc	ppm	ASTM D5185m	1270	<b>1290</b>	1247	1142
Sulfur	ppm	ASTM D5185m	2060	<b>3484</b>	3138	3278
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>16.5</b>	15.3	14.0
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>7.2</b>	7.7	8.0
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.2</b>	13.3	13.4


**FT-IR (Direct Trend)**




**Base Number**




**Viscosity @ 100°C**




**Ferrous Alloys**




**Non-ferrous Metals**



**Viscosity @ 100°C**



**Base Number**



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : GFL0127792  
**Lab Number** : 06240054  
**Unique Number** : 11128888  
**Test Package** : FLEET

**Received** : 18 Jul 2024  
**Tested** : 19 Jul 2024  
**Diagnosed** : 19 Jul 2024 - Wes Davis

**GFL Environmental - 084 - Clarksville**  
 699 Jack Miller Boulevard  
 Clarksville, TN  
 US 37042

Contact: ROBERT THIBAUT  
 robert.thibault@gflenv.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (931)552-7276  
 F: (931)572-9674