



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Machine Id
pm 061248 (S/N A37586)
 Component
Diesel Engine
 Fluid
DIESEL ENGINE OIL SAE 40 (40 QTS)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0221321	JR0210306	---
Sample Date		Client Info		15 Jul 2024	07 Mar 2024	---
Machine Age	hrs	Client Info		5946	5444	---
Oil Age	hrs	Client Info		5444	5444	---
Filter Age	hrs	Client Info		5444	5444	---
Oil Changed		Client Info		Changed	Changed	---
Filter Changed		Client Info		Changed	Changed	---
Sample Status				NORMAL	NORMAL	---

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>100	11	12	---
Chromium	ppm	ASTM D5185m	>20	<1	<1	---
Nickel	ppm	ASTM D5185m	>4	0	<1	---
Titanium	ppm	ASTM D5185m		<1	<1	---
Silver	ppm	ASTM D5185m	>3	0	<1	---
Aluminum	ppm	ASTM D5185m	>20	3	2	---
Lead	ppm	ASTM D5185m	>40	<1	<1	---
Copper	ppm	ASTM D5185m	>330	1	2	---
Tin	ppm	ASTM D5185m	>15	0	<1	---
Vanadium	ppm	ASTM D5185m		0	<1	---
White Metal	scalar	*Visual	NONE	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---

CONTAMINATION








There is no indication of any contamination in the oil.

Silicon	ppm	ASTM D5185m	>25	6	5	---
Potassium	ppm	ASTM D5185m	>20	3	2	---
Fuel		WC Method	>5	<1.0	<1.0	---
Water		WC Method	>0.2	NEG	NEG	---
Glycol		WC Method		NEG	NEG	---
Soot %	%	*ASTM D7844	>3	0.7	0.6	---
Nitration	Abs/cm	*ASTM D7624	>20	10.1	9.0	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.7	20.5	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	---

FLUID CONDITION

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>216	5	0	---
Boron	ppm	ASTM D5185m	250	148	72	---
Barium	ppm	ASTM D5185m	10	0	0	---
Molybdenum	ppm	ASTM D5185m	100	229	68	---
Manganese	ppm	ASTM D5185m		<1	<1	---
Magnesium	ppm	ASTM D5185m	450	816	409	---
Calcium	ppm	ASTM D5185m	3000	1794	1846	---
Phosphorus	ppm	ASTM D5185m	1150	1009	1094	---
Zinc	ppm	ASTM D5185m	1350	1218	1265	---
Sulfur	ppm	ASTM D5185m	4250	3809	3494	---
Oxidation	Abs/.1mm	*ASTM D7414	>25	19.0	17.7	---
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	8.2	7.8	---
Visc @ 100°C	cSt	ASTM D445	14.4	14.0	13.5	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : JR0221321 **Received** : 18 Jul 2024
Lab Number : 06240149 **Tested** : 19 Jul 2024
Unique Number : 11128983 **Diagnosed** : 19 Jul 2024 - Wes Davis
Test Package : CONST (Additional Tests: TBN)

JRE - STEPHENSON
 245 YARDMASTER COURT
 STEPHENSON, VA
 US 22656-1761
 Contact: PHIL DAUGHERTY
 pdaugherty@jamesriverequipment.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: x:
 F: (540)693-2588