



# OIL ANALYSIS REPORT

WEAR	NORMAL
CONTAMINATION	ATTENTION
FLUID CONDITION	NORMAL

Machine Id  
**6474 6474**  
 Component  
**Gearbox**  
 Fluid  
**GEAR OIL SAE 85W140 (--- GAL)**

## RECOMMENDATION

Resample at the next service interval to monitor.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		WC0937851	---	---
Sample Date		Client Info		16 Jul 2024	---	---
Machine Age	hrs	Client Info		66	---	---
Oil Age	hrs	Client Info		66	---	---
Filter Age	hrs	Client Info		66	---	---
Oil Changed		Client Info		Not Changd	---	---
Filter Changed		Client Info		Not Changd	---	---
Sample Status				ATTENTION	---	---

## WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>200	11	---	---
Chromium	ppm	ASTM D5185m	>10	<1	---	---
Nickel	ppm	ASTM D5185m	>10	0	---	---
Titanium	ppm	ASTM D5185m		<1	---	---
Silver	ppm	ASTM D5185m		<1	---	---
Aluminum	ppm	ASTM D5185m	>25	4	---	---
Lead	ppm	ASTM D5185m	>50	0	---	---
Copper	ppm	ASTM D5185m	>200	2	---	---
Tin	ppm	ASTM D5185m	>10	<1	---	---
Vanadium	ppm	ASTM D5185m		<1	---	---
White Metal	scalar	*Visual	NONE	NONE	---	---
Yellow Metal	scalar	*Visual	NONE	NONE	---	---

## CONTAMINATION










There is a moderate amount of particulates present in the oil.

Silicon	ppm	ASTM D5185m	>50	5	---	---
Potassium	ppm	ASTM D5185m	>20	2	---	---
Water		WC Method	>0.2	NEG	---	---
Particles >4µm		ASTM D7647	>20000	9770	---	---
Particles >6µm		ASTM D7647	>5000	5322	---	---
Particles >14µm		ASTM D7647	>640	906	---	---
Particles >21µm		ASTM D7647	>160	305	---	---
Particles >38µm		ASTM D7647	>40	47	---	---
Particles >71µm		ASTM D7647	>10	5	---	---
Oil Cleanliness		ISO 4406 (c)	>21/19/16	20/20/17	---	---
Silt	scalar	*Visual	NONE	NONE	---	---
Debris	scalar	*Visual	NONE	NONE	---	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---	---
Appearance	scalar	*Visual	NORML	NORML	---	---
Odor	scalar	*Visual	NORML	NORML	---	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---	---

## FLUID CONDITION

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185m		0	---	---
Boron	ppm	ASTM D5185m	400	208	---	---
Barium	ppm	ASTM D5185m	200	9	---	---
Molybdenum	ppm	ASTM D5185m	12	2	---	---
Manganese	ppm	ASTM D5185m		<1	---	---
Magnesium	ppm	ASTM D5185m	12	27	---	---
Calcium	ppm	ASTM D5185m	150	75	---	---
Phosphorus	ppm	ASTM D5185m	1650	950	---	---
Zinc	ppm	ASTM D5185m	125	56	---	---
Sulfur	ppm	ASTM D5185m	22500	21692	---	---
Visc @ 40°C	cSt	ASTM D445	368	320	---	---



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
 Sample No. : WC0937851 Received : 18 Jul 2024  
 Lab Number : 06240172 Tested : 19 Jul 2024  
 Unique Number : 11129006 Diagnosed : 19 Jul 2024 - Don Baldrige  
 Test Package : CONST ( Additional Tests: PrtCount )

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

**CAROLINA SUNROCK**

PO BOX 25  
 BUTNER, NC  
 US 27509

Contact: Leigh Dennis  
 rdennis@thesunrockgroup.com

T: (919)575-4505

F: (919)575-0162