

# [W68867]

# JOHN DEERE 350P 1E 1FF350PAHPF001028

Swing Drive

## JOHN DEERE GL-5 80W90 (2 GAL)

### RECOMMENDATION

Resample at the next service interval to monitor. ( Customer Sample Comment: W68867 )

#### **WEAR**

All component wear rates are normal.

\_\_\_\_\_

#### CONTAMINATION


There is no indication of any contamination in the oil.


### **FLUID CONDITION**


The condition of the oil is acceptable for the time in service.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		JR0220723		
Sample Date		Client Info		16 Jul 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Filter Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Filter Changed		Client Info		Not Changd		
Sample Status				NORMAL		
<b>DO</b>						
PQ		ASTM D8184	454	36		
Iron	ppm	ASTM D5185m	>151	65		
Chromium	ppm	ASTM D5185m	>11	1		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		<1		
Aluminum	ppm	ASTM D5185m	>21	4		
Lead	ppm	ASTM D5185m	>51	0		
Copper	ppm	ASTM D5185m	>51	<1		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Silicon	ppm	ASTM D5185m	>31	19		
Potassium	ppm	ASTM D5185m	>20	2		
Water		WC Method	>0.1	NEG		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Sodium	ppm	ASTM D5185m	>51	<1		
Boron	ppm	ASTM D5185m		105		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m		1		
Calcium	ppm	ASTM D5185m		8		
Phosphorus	ppm	ASTM D5185m		605		
Zinc	ppm	ASTM D5185m		9		
Sulfur	ppm	ASTM D5185m		18015		
Visc @ 40°C						

Submitted By: Mike Young - CHARLOTTE SHOP







Submitted By: Mike Young - CHARLOTTE SHOP Page 2 of 2