James River Equipment
OIL ANALYSIS REPORT

WEAR	**NORMAL**
CONTAMINATION	**NORMAL**
FLUID CONDITION	**NORMAL**

Machine Id
JOHN DEERE 324G 1T0324GMHRJ458482
Component
Right Chain Case
Fluid
JOHN DEERE HY-GARD HYD/TRANS (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor.

WEAR

All component wear rates are normal.

CONTAMINATION

There is no indication of any contamination in the oil.

FLUID CONDITION

The condition of the oil is acceptable for the time in service.

| Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		**JR0221146**	---	---
Sample Date		Client Info		**15 Jul 2024**	---	---
Machine Age	hrs	Client Info		**16**	---	---
Oil Age	hrs	Client Info		**16**	---	---
Filter Age	hrs	Client Info		**0**	---	---
Oil Changed		Client Info		**Not Changd**	---	---
Filter Changed		Client Info		**Not Changd**	---	---
Sample Status				**NORMAL**	---	---
PQ		ASTM D8184		**19**	---	---
Iron	ppm	ASTM D5185m	>632	**95**	---	---
Chromium	ppm	ASTM D5185m	>3	**<1**	---	---
Nickel	ppm	ASTM D5185m	>3	**0**	---	---
Titanium	ppm	ASTM D5185m		**<1**	---	---
Silver	ppm	ASTM D5185m		**<1**	---	---
Aluminum	ppm	ASTM D5185m	>19	**4**	---	---
Lead	ppm	ASTM D5185m	>6	**0**	---	---
Copper	ppm	ASTM D5185m	>46	**4**	---	---
Tin	ppm	ASTM D5185m	>3	**<1**	---	---
Vanadium	ppm	ASTM D5185m		**<1**	---	---
White Metal	scalar	*Visual	NONE	**NONE**	---	---
Yellow Metal	scalar	*Visual	NONE	**NONE**	---	---
Silicon	ppm	ASTM D5185m	>82	**16**	---	---
Potassium	ppm	ASTM D5185m	>20	**3**	---	---
Water		WC Method	>0.2	**NEG**	---	---
Silt	scalar	*Visual	NONE	**NONE**	---	---
Debris	scalar	*Visual	NONE	**NONE**	---	---
Sand/Dirt	scalar	*Visual	NONE	**NONE**	---	---
Appearance	scalar	*Visual	NORML	**NORML**	---	---
Odor	scalar	*Visual	NORML	**NORML**	---	---
Emulsified Water	scalar	*Visual	>0.2	**NEG**	---	---
Sodium	ppm	ASTM D5185m		**0**	---	---
Boron	ppm	ASTM D5185m	6	**<1**	---	---
Barium	ppm	ASTM D5185m	0	**20**	---	---
Molybdenum	ppm	ASTM D5185m	0	**3**	---	---
Manganese	ppm	ASTM D5185m		**1**	---	---
Magnesium	ppm	ASTM D5185m	145	**104**	---	---
Calcium	ppm	ASTM D5185m	3570	**3642**	---	---
Phosphorus	ppm	ASTM D5185m	1290	**1023**	---	---
Zinc	ppm	ASTM D5185m	1640	**1245**	---	---
Sulfur	ppm	ASTM D5185m		**3616**	---	---
Visc @ 40°C	cSt	ASTM D445	57.0	**59.3**	---	---

Viscosity @ 40°C

cSt (40°C)

Abnormal
Base
Abnormal

Jul15/24 — Jul15/24

PQ

PQ

Severe
Abnormal

Jul15/24 — Jul15/24

Ferrous Alloys

ppm

— iron
— chromium
— nickel

Jul15/24 — Jul15/24

Non-ferrous Metals

ppm

— copper
— lead
— tin

Jul15/24 — Jul15/24

Viscosity @ 40°C

cSt (40°C)

Abnormal
Base
Abnormal

Jul15/24 — Jul15/24

PQ

PQ

Severe
Abnormal

Jul15/24 — Jul15/24

JRE - STEPHENSON
245 YARDMASTER COURT
STEPHENSON, VA
US 22656-1761
Contact: PHIL DAUGHERTY
pdaugherty@jamesriverequipment.com
T: x:
F: (540)693-2588

ANAB ACCREDITED
ISO/IEC 17025
TESTING LABORATORY
Certificate L2367

To discuss this sample report, contact Customer Service at 1-800-237-1369.
* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)