

## JOHN DEERE 410K 7014 (S/N 1T0410KXCEE269961)

**Front Differential** 


## JOHN DEERE HY-GARD HYD/TRANS (--- QTS)


JOHN DEERE HY-GARD HYD/IRANS ( QIS	<i>?)</i>						
RECOMMENDATION	Test	UOM	Method	Limit/Abn	Current	History1	History2
Resample at the next service interval to monitor.	Sample Number		Client Info		JR0226519		
	Sample Date		Client Info		17 Jul 2024		
	Machine Age	hrs	Client Info		8531		
	Oil Age	hrs	Client Info		8531		
	Filter Age	hrs	Client Info		0		
	Oil Changed		Client Info		Not Changd		
	Filter Changed		Client Info		None		
	Sample Status				NORMAL		
WEAR	PQ		ASTM D8184		86		
	Iron	ppm	ASTM D5185m	>500	80		
All component wear rates are normal.	Chromium	ppm	ASTM D5185m		<1		
	Nickel	ppm	ASTM D5185m		0		
	Titanium	ppm	ASTM D5185m		<1		
	Silver	ppm	ASTM D5185m		<1		
	Aluminum	ppm	ASTM D5185m	>25	4		
	Lead	ppm	ASTM D5185m	>25	0		
	Copper	ppm	ASTM D5185m	>100	22		
	Tin	ppm	ASTM D5185m	>10	<1		
	Vanadium	ppm	ASTM D5185m		<1		
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
CONTAMINATION	Silicon	ppm	ASTM D5185m	>75	2		
There is no indication of any contamination in the oil.	Potassium	ppm	ASTM D5185m		-		
	Water	1-1-	WC Method		NEG		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>.2	NEG		
FLUID CONDITION	Sodium	ppm	ASTM D5185m		0		
Confirm oil type. The condition of the oil is acceptable for the time in service.	Boron	ppm	ASTM D5185m	6	341		
	Barium	ppm	ASTM D5185m		0		
	Molybdenum	ppm	ASTM D5185m	0	3		
	Manganese	ppm	ASTM D5185m		<1		
	Magnesium	ppm	ASTM D5185m	145	1		
	Calcium	ppm	ASTM D5185m	3570	89		
	Phosphorus	ppm	ASTM D5185m	1290	2200		
	Zinc	ppm	ASTM D5185m	1640	44		
	Sulfur	ppm	ASTM D5185m		25439		


Visc @ 40°C

cSt

ASTM D445 57.0 56.8 --- ---Submitted By: TECHNICIAN ACCOUNT







Submitted By: TECHNICIAN ACCOUNT Page 2 of 2