



WEAR	NORMAL
CONTAMINATION	NORMAL
FLUID CONDITION	NORMAL

Area
RICH MCCARTY
Machine Id
RICH MCCARTY
Component
Port Main Engine
Fluid
CHEVRON DELO 710 LS (350 GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Sample Number		Client Info		MW0057496	MW0057506	MW0057636
Sample Date		Client Info		15 Jul 2024	30 Jun 2024	15 May 2024
Machine Age	hrs	Client Info		44882	44546	43467
Oil Age	hrs	Client Info		4874	4538	3459
Filter Age	hrs	Client Info		475	134	491
Oil Changed		Client Info		N/A	Not Changed	Changed
Filter Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL

WEAR

All component wear rates are normal.

Iron	ppm	ASTM D5185m	>75	14	16	12
Chromium	ppm	ASTM D5185m	>8	<1	2	<1
Nickel	ppm	ASTM D5185m	>2	0	<1	0
Titanium	ppm	ASTM D5185m	>3	0	1	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>15	1	3	2
Lead	ppm	ASTM D5185m	>18	2	4	3
Copper	ppm	ASTM D5185m	>80	13	15	11
Tin	ppm	ASTM D5185m	>14	2	4	3
Vanadium	ppm	ASTM D5185m		0	<1	0
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicon	ppm	ASTM D5185m	>20	3	5	4
Potassium	ppm	ASTM D5185m	>20	0	3	0
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
Soot %	%	*ASTM D7844		1	0.9	0.8
Nitration	Abs/cm	*ASTM D7624	>20	8.9	8.6	8.1
Sulfation	Abs/.1mm	*ASTM D7415	>30	17.5	16.7	18.0
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG

FLUID CONDITION


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

Sodium	ppm	ASTM D5185m	>75	4	12	11
Boron	ppm	ASTM D5185m		36	41	46
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		45	48	48
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		12	11	7
Calcium	ppm	ASTM D5185m		3496	3602	3490
Phosphorus	ppm	ASTM D5185m		5	12	0
Zinc	ppm	ASTM D5185m		<1	<1	0
Sulfur	ppm	ASTM D5185m		2499	2302	2431
Oxidation	Abs/.1mm	*ASTM D7414	>25	8.9	8.5	11.1
Base Number (BN)	mg KOH/g	ASTM D2896	10.5	6.1	6.6	6.4
Visc @ 100°C	cSt	ASTM D445	15.5	14.7	14.9	14.8


FT-IR (Direct Trend)




Base Number




Viscosity @ 100°C




Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : MW0057496
Lab Number : 06241510
Unique Number : 11130344
Test Package : MAR 2

Received : 19 Jul 2024
Tested : 22 Jul 2024
Diagnosed : 22 Jul 2024 - Wes Davis

AMERICAN RIVER TRANSPORTATION CO.
 P.O. BOX 2889
 ST. LOUIS, MO
 US 63111
 Contact: BRIAN GRIEWING
 brian.griewing@adm.com
 T:
 F: (314)481-5278

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)