



USURE	ANORMAL
CONTAMINATION	NORMAL
ÉTAT DU FLUIDE	NORMAL

Secteur
MICHAUDVILLE
Identité de la machine
1223
Composant
Transmission (Auto)
Fluide
DEXRON III (--- GAL)

RECOMMENDATION

We recommend that you drain the fluid from the component if this has not already been done. We recommend an early resample to monitor this condition. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DEXRON III. Please confirm. Please specify the component make and model with your next sample.

USURE

Aluminum ppm levels are abnormal. Torque converter wear is indicated.












CONTAMINATION

There is no indication of any contamination in the fluid.

ÉTAT DU FLUIDE

The fluid is no longer serviceable as a result of the abnormal and/or severe wear.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Numéro d'échant.		Client Info		PC0071943	PC0070803	PC0066488
Date d'échant.		Client Info		24 Jul 2023	12 Mar 2023	17 Nov 2022
Âge d la Machine	hrs	Client Info		8832	8305	7857
Âge de l'huile	hrs	Client Info		0	0	0
Âge du filtre	hrs	Client Info		0	0	0
Huile changée		Client Info		N/A	N/A	N/A
Filtre changé		Client Info		N/A	N/A	N/A
Statut de l'échant.				ABNORMAL	ABNORMAL	NORMAL
Fer	ppm	ASTM D5185(m)	>160	124	138	111
Chrome	ppm	ASTM D5185(m)	>5	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	<1	<1	<1
Titane	ppm	ASTM D5185(m)		0	<1	0
Argent	ppm	ASTM D5185(m)	>5	0	0	0
Aluminium	ppm	ASTM D5185(m)	>50	▲ 69	▲ 71	56
Plomb	ppm	ASTM D5185(m)	>50	17	18	17
Cuivre	ppm	ASTM D5185(m)	>225	22	21	18
Étain	ppm	ASTM D5185(m)	>10	6	6	5
Vanadium	ppm	ASTM D5185(m)		0	0	0
Métal blanc	scalar	Visual*	NONE	NONE	NONE	NONE
Bronze	scalar	Visual*	NONE	NONE	NONE	NONE
Silicium	ppm	ASTM D5185(m)	>20	14	15	13
Potassium	ppm	ASTM D5185(m)	>20	2	2	2
Limon	scalar	Visual*	NONE	VLITE	VLITE	NONE
Débris	scalar	Visual*	NONE	NONE	NONE	NONE
Saleté	scalar	Visual*	NONE	NONE	NONE	NONE
Apparence	scalar	Visual*	NORML	NORML	NORML	NORML
Odeur	scalar	Visual*	NORML	NORML	NORML	NORML
Eau émulsifiée	scalar	Visual*	>0.1	NEG	NEG	NEG
Sodium	ppm	ASTM D5185(m)		4	5	5
Bore	ppm	ASTM D5185(m)		63	70	69
Baryum	ppm	ASTM D5185(m)		0	0	0
Molybdène	ppm	ASTM D5185(m)		<1	<1	0
Manganèse	ppm	ASTM D5185(m)		2	2	2
Magnésium	ppm	ASTM D5185(m)		1	1	<1
Calcium	ppm	ASTM D5185(m)		96	101	98
Phosphore	ppm	ASTM D5185(m)		224	244	235
Zinc	ppm	ASTM D5185(m)		6	5	5
Soufre	ppm	ASTM D5185(m)		1071	1343	1059
Visc 40°C	cSt	ASTM D7279(m)	26.0	32.7	32.7	33.0
Visc 100°C	cSt	ASTM D7279(m)	5.5	6.4	6.5	6.5
Indice de viscosité (VI)	Scale	ASTM D2270*	155	151	157	154



ISO 17025:2017
Accredited
Laboratory

Laboratoire : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 **LES ENTREPRISES MICHAUVILLE INC.**
N° d'échantillon : PC0071943 **Reçu** : 25 Jul 2023 270 RUE BRUNET
N° de laboratoire : 02571976 **Diagnostiqué** : 26 Jul 2023 MONT ST-HILAIRE, QC
Numéro unique : 5617027 **Diagnostiqueur** : Kevin Marson CA J3H 0M6
Analyse : MOB 1 (Additional Tests: KV100, VI) Contact: Martin Trudel

Pour discuter ce rapport, contacter le service à la clientèle au 1-800-268-2131. mtrudel@michaudville.com
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab. T:
 La validez de los resultados y la interpretación se basan en la muestra y la información proporcionada. F: