



RAPPORT D'ANALYSE D'HUILE

USURE	NORMAL
CONTAMINATION	NORMAL
ÉTAT DU FLUIDE	NORMAL

Secteur
MICHAUDVILLE

Identité de la machine

1587

Composant

Moteur diesel

Fluide

DIESEL ENGINE OIL SAE 10W30 (--- GAL)

RECOMMENDATION

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Numéro d'échant.		Client Info		PC0077369	PC0070866	PC0070806
Date d'échant.		Client Info		25 Jul 2023	16 Apr 2023	12 Mar 2023
Âge d la Machine	hrs	Client Info		15332	14823	14784
Âge de l'huile	hrs	Client Info		0	0	0
Âge du filtre	hrs	Client Info		0	0	0
Huile changée		Client Info		N/A	N/A	N/A
Filtre changé		Client Info		N/A	N/A	N/A
Statut de l'échant.				NORMAL	NORMAL	NORMAL

USURE

All component wear rates are normal.

Fer	ppm	ASTM D5185(m)	>100	17	6	26
Chrome	ppm	ASTM D5185(m)	>20	<1	0	<1
Nickel	ppm	ASTM D5185(m)	>4	0	<1	<1
Titane	ppm	ASTM D5185(m)		0	0	<1
Argent	ppm	ASTM D5185(m)	>3	0	0	0
Aluminium	ppm	ASTM D5185(m)	>20	8	1	2
Plomb	ppm	ASTM D5185(m)	>40	7	<1	1
Cuivre	ppm	ASTM D5185(m)	>330	2	<1	<1
Étain	ppm	ASTM D5185(m)	>15	<1	<1	<1
Vanadium	ppm	ASTM D5185(m)		0	0	0

CONTAMINATION











Elevated aluminum (Al) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.

Silicium	ppm	ASTM D5185(m)	>25	8	5	6
Potassium	ppm	ASTM D5185(m)	>20	23	0	1
Essence		WC Method	>5	<1.0	<1.0	<1.0
Glycol		WC Method		NEG	NEG	NEG
% de suie	%	ASTM D7844*	>3	0	0	0.6
Nitration	Abs/cm	ASTM D7624*	>20	10.4	5.6	10.5
Sulfatation	Abs/.1mm	ASTM D7415*	>30	22.6	18.8	23.6
Eau émulsifiée	scalar	Visual*	>0.2	NEG	NEG	NEG

ÉTAT DU FLUIDE

The condition of the oil is acceptable for the time in service.

Sodium	ppm	ASTM D5185(m)		5	2	5
Bore	ppm	ASTM D5185(m)	250	2	2	2
Baryum	ppm	ASTM D5185(m)	10	0	0	0
Molybdène	ppm	ASTM D5185(m)	100	60	58	62
Manganèse	ppm	ASTM D5185(m)		<1	<1	<1
Magnésium	ppm	ASTM D5185(m)	450	1025	929	1003
Calcium	ppm	ASTM D5185(m)	3000	1144	1102	1188
Phosphore	ppm	ASTM D5185(m)	1150	1105	1078	1125
Zinc	ppm	ASTM D5185(m)	1350	1261	1158	1252
Soufre	ppm	ASTM D5185(m)	4250	2533	2681	2691
Oxydation	Abs/.1mm	ASTM D7414*	>25	19.7	13.6	17.4
Visc 40°C	cSt	ASTM D7279(m)	73	94.0	97.5	94.0
Visc 100°C	cSt	ASTM D7279(m)	10.9	13.7	14.3	13.6
Indice de viscosité (VI)	Scale	ASTM D2270*	138	147	150	146



ISO 17025:2017
Accredited
Laboratory

Laboratoire : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 LES ENTREPRISES MICHAUDVILLE INC.
N° d'échantillon : PC0077369 **Reçu** : 26 Jul 2023
N° de laboratoire : 02572136 **Diagnostiqué** : 26 Jul 2023
Numéro unique : 5617187 **Diagnostiqueur** : Wes Davis
Analyse : MOB 1 (Additional Tests: KV40, VI)

Pour discuter ce rapport, contacter le service à la clientèle au 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

La validez de los resultados y la interpretación se basan en la muestra y la información proporcionada.

270 RUE BRUNET
MONT ST-HILAIRE, QC
CA J3H 0M6
Contact: Martin Trudel
mtrudel@michaudville.com

T:
F: