



USURE	ANORMAL
CONTAMINATION	NORMAL
ÉTAT DU FLUIDE	NORMAL

Secteur
MICHAUDVILLE

Identité de la machine

1202

Composant

Transmission (Auto)

Fluide

DEXRON III (--- GAL)

RECOMMENDATION

We recommend that you drain the fluid from the component if this has not already been done. We recommend an early resample to monitor this condition. The fluid was not specified, however, a fluid match indicates that this fluid is (GENERIC) DEXRON III. Please confirm. Please specify the component make and model with your next sample.

USURE

Iron and lead ppm levels are abnormal. Clutch disc wear indicated. The low ferrous density (PQ) index indicates the wear metal levels are due to corrosion.

CONTAMINATION


There is no indication of any contamination in the fluid.

ÉTAT DU FLUIDE


The fluid is no longer serviceable as a result of the abnormal and/or severe wear.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Numéro d'échant.		Client Info		PC0082245	PC0075808	PC0056537
Date d'échant.		Client Info		20 Sep 2023	07 Jun 2023	24 Jan 2023
Âge d la Machine	hrs	Client Info		12197	11736	270956
Âge de l'huile	hrs	Client Info		0	0	0
Âge du filtre	hrs	Client Info		0	0	0
Huile changée		Client Info		N/A	N/A	N/A
Filtre changé		Client Info		N/A	N/A	N/A
Statut de l'échant.				ABNORMAL	ABNORMAL	ATTENTION
PQ		ASTM D8184*	>50	9	13	6
Fer	ppm	ASTM D5185(m)	>160	▲ 199	▲ 208	▲ 180
Chrome	ppm	ASTM D5185(m)	>5	<1	<1	<1
Nickel	ppm	ASTM D5185(m)	>5	<1	0	<1
Titane	ppm	ASTM D5185(m)		0	0	0
Argent	ppm	ASTM D5185(m)	>5	0	0	0
Aluminium	ppm	ASTM D5185(m)	>50	26	30	27
Plomb	ppm	ASTM D5185(m)	>50	▲ 61	▲ 65	57
Cuivre	ppm	ASTM D5185(m)	>225	29	32	29
Étain	ppm	ASTM D5185(m)	>10	3	4	3
Vanadium	ppm	ASTM D5185(m)		0	0	0
Métal blanc	scalar	Visual*	NONE	NONE	NONE	NONE
Bronze	scalar	Visual*	NONE	NONE	NONE	NONE
Silicium	ppm	ASTM D5185(m)	>20	7	8	7
Potassium	ppm	ASTM D5185(m)	>20	2	2	2
Limon	scalar	Visual*	NONE	NONE	NONE	NONE
Débris	scalar	Visual*	NONE	NONE	NONE	NONE
Saleté	scalar	Visual*	NONE	NONE	NONE	NONE
Apparence	scalar	Visual*	NORML	NORML	NORML	NORML
Odeur	scalar	Visual*	NORML	NORML	NORML	NORML
Eau émulsifiée	scalar	Visual*	>0.1	NEG	NEG	NEG
Sodium	ppm	ASTM D5185(m)		9	10	10
Bore	ppm	ASTM D5185(m)		146	173	162
Baryum	ppm	ASTM D5185(m)		0	0	0
Molybdène	ppm	ASTM D5185(m)		<1	0	0
Manganèse	ppm	ASTM D5185(m)		2	2	2
Magnésium	ppm	ASTM D5185(m)		<1	<1	<1
Calcium	ppm	ASTM D5185(m)		129	137	133
Phosphore	ppm	ASTM D5185(m)		430	473	451
Zinc	ppm	ASTM D5185(m)		17	18	16
Soufre	ppm	ASTM D5185(m)		1994	2231	2141
Visc 40°C	cSt	ASTM D7279(m)	26.0	34.4	34.5	34.6
Visc 100°C	cSt	ASTM D7279(m)	5.5	6.8	6.8	6.9
Indice de viscosité (VI)	Scale	ASTM D2270*	155	160	158	161


▲ Métaux non-ferreux




▲ Fer (ppm)




▲ Plomb (ppm)




▲ Alliages ferreux




Aluminium (ppm)




Chrome (ppm)




Viscosité 100°C




Cuivre (ppm)




Silicium (ppm)




Viscosité 40°C




Viscosité 40°C



PQ



PQ



Laboratoire : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9 LES ENTREPRISES MICHAUVILLE INC.
N° d'échantillon : PC0082245 **Reçu** : 21 Sep 2023
N° de laboratoire : 02584457 **Diagnostiqué** : 25 Sep 2023
Numéro unique : 5645522 **Diagnostiqueur** : Bill Quesnel
Analyse : MOB 1 (Additional Tests: KV100, PQ, VI)

Pour discuter ce rapport, contacter le service à la clientèle au 1-800-268-2131.

Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

La validez de los resultados y la interpretación se basan en la muestra y la información proporcionada.

270 RUE BRUNET
 MONT ST-HILAIRE, QC
 CA J3H 0M6
 Contact: Martin Trudel
 mtrudel@michaudville.com

T:
 F: