



USURE	<b>NORMAL</b>
CONTAMINATION	<b>ANORMAL</b>
ÉTAT DU FLUIDE	<b>NORMAL</b>

Identité de la machine

**90204**

Composant

**Compresseur**

Fluid

{not provided} (--- GAL)

**RECOMMENDATION**

We advise that you check for the source of water entry. Check seals and/or filters for points of contaminant entry. The air breather requires service. If unrated, we recommend that you replace with a suitable micron rated and/or desiccant air breather. If rated, we recommend that you service/replace the breather. We recommend that you drain the oil from the component if this has not already been done. We recommend an early resample to monitor this condition. Please specify the brand, type, and viscosity of the oil on your next sample. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

**USURE**

All component wear rates are normal.

**CONTAMINATION**

There is a moderate concentration of water present in the oil.

**ÉTAT DU FLUIDE**

The oil is no longer serviceable due to the presence of contaminants.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Numéro d'échant.		Client Info		<b>PC0083768</b>	---	---
Date d'échant.		Client Info		<b>20 Mar 2024</b>	---	---
Âge d la Machine	hrs	Client Info		<b>1679</b>	---	---
Âge de l'huile	hrs	Client Info		<b>0</b>	---	---
Âge du filtre	hrs	Client Info		<b>0</b>	---	---
Huile changée		Client Info		<b>N/A</b>	---	---
Filtre changé		Client Info		<b>N/A</b>	---	---
Statut de l'échant.				<b>ABNORMAL</b>	---	---
Fer	ppm	ASTM D5185(m)	>50	<b>3</b>	---	---
Chrome	ppm	ASTM D5185(m)	>5	<b>0</b>	---	---
Nickel	ppm	ASTM D5185(m)		<b>&lt;1</b>	---	---
Titane	ppm	ASTM D5185(m)		<b>0</b>	---	---
Argent	ppm	ASTM D5185(m)		<b>0</b>	---	---
Aluminium	ppm	ASTM D5185(m)	>15	<b>0</b>	---	---
Plomb	ppm	ASTM D5185(m)	>65	<b>0</b>	---	---
Cuivre	ppm	ASTM D5185(m)	>65	<b>2</b>	---	---
Étain	ppm	ASTM D5185(m)	>10	<b>0</b>	---	---
Vanadium	ppm	ASTM D5185(m)		<b>0</b>	---	---
Métal blanc	scalar	Visual*	NONE	<b>NONE</b>	---	---
Bronze	scalar	Visual*	NONE	<b>NONE</b>	---	---
Silicium	ppm	ASTM D5185(m)	>35	<b>6</b>	---	---
Potassium	ppm	ASTM D5185(m)	>20	<b>6</b>	---	---
Eau	%	ASTM D6304*	>0.1	<b>▲ 0.280</b>	---	---
ppm d'eau	ppm	ASTM D6304*	>1000	<b>▲ 2802</b>	---	---
Limon	scalar	Visual*	NONE	<b>NONE</b>	---	---
Débris	scalar	Visual*	NONE	<b>NONE</b>	---	---
Saleté	scalar	Visual*	NONE	<b>NONE</b>	---	---
Apparence	scalar	Visual*	NORML	<b>NORML</b>	---	---
Odeur	scalar	Visual*	NORML	<b>NORML</b>	---	---
Eau émulsifiée	scalar	Visual*	>0.1	<b>▲ .2%</b>	---	---
Sodium	ppm	ASTM D5185(m)		<b>20</b>	---	---
Bore	ppm	ASTM D5185(m)		<b>0</b>	---	---
Baryum	ppm	ASTM D5185(m)		<b>2</b>	---	---
Molybdène	ppm	ASTM D5185(m)		<b>0</b>	---	---
Manganèse	ppm	ASTM D5185(m)		<b>0</b>	---	---
Magnésium	ppm	ASTM D5185(m)		<b>5</b>	---	---
Calcium	ppm	ASTM D5185(m)		<b>932</b>	---	---
Phosphore	ppm	ASTM D5185(m)		<b>878</b>	---	---
Zinc	ppm	ASTM D5185(m)		<b>1019</b>	---	---
Soufre	ppm	ASTM D5185(m)		<b>2647</b>	---	---
Visc 40°C	cSt	ASTM D7279(m)		<b>32.2</b>	---	---
Visc 100°C	cSt	ASTM D7279(m)		<b>6.1</b>	---	---
Indice de viscosité (VI)	Scale	ASTM D2270*		<b>139</b>	---	---



**Laboratoire** : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9  
**N° d'échantillon** : PC0083768  
**N° de laboratoire** : 02623734  
**Numéro unique** : 5748853  
**Analyse** : MOB 1 ( Additional Tests: KF, KV100, VI )

**LES ENTREPRISES MICHAUDVILLE INC.**  
 270 RUE BRUNET  
 MONT ST-HILAIRE, QC  
 CA J3H 0M6  
 Contact: Martin Trudel  
 mtrudel@michaudville.com

Pour discuter ce rapport, contacter le service à la clientèle au 1-800-268-2131.

Test denoted (\*) outside scope of accreditation, (m) method modified, (e) tested at external lab.

La validez de los resultados y la interpretación se basan en la muestra y la información proporcionada.

T:  
F: