



RAPPORT D'ANALYSE D'HUILE

USURE	NORMAL
CONTAMINATION	NORMAL
ÉTAT DU FLUIDE	NORMAL

Secteur

Equipment de Pont

Identité de la machine

17DA02 DE Guindeau/Engrenage (S/N C-1084)

Composant

Boîte d'engrenages Avant

Fluid

MOBIL SHC 629 (200 LTR)

RECOMMENDATION

Resample at the next service interval to monitor. Please contact your representative for information regarding the proper sampling kits for your service. NOTE: We recommend using MAR 2 test kits, this testkit includes AN to determine the suitability of the oil for continued use.

Test	UOM	Method	Limit/Abn	Current	History1	History2
Numéro d'échant.		Client Info		WC0878509	WC0811224	WC0549537
Date d'échant.		Client Info		20 Mar 2024	25 Oct 2023	02 Apr 2023
Âge d la Machine	hrs	Client Info		0	0	0
Âge de l'huile	hrs	Client Info		0	0	0
Âge du filtre	hrs	Client Info		0	0	0
Huile changée		Client Info		Not Chngd	N/A	Not Chngd
Filtre changé		Client Info		Not Chngd	N/A	Not Chngd
Statut de l'échant.				NORMAL	NORMAL	NORMAL

USURE

All component wear rates are normal.

Fer	ppm	ASTM D5185(m)	>150	3	4	4
Chrome	ppm	ASTM D5185(m)	>10	0	0	0
Nickel	ppm	ASTM D5185(m)	>10	0	0	<1
Titane	ppm	ASTM D5185(m)		0	0	0
Argent	ppm	ASTM D5185(m)		0	<1	0
Aluminium	ppm	ASTM D5185(m)	>5	0	0	0
Plomb	ppm	ASTM D5185(m)	>65	0	<1	<1
Cuivre	ppm	ASTM D5185(m)	>80	<1	<1	<1
Étain	ppm	ASTM D5185(m)	>8	0	0	0
Vanadium	ppm	ASTM D5185(m)		0	0	0
Métal blanc	scalar	Visual*	NONE	NONE	NONE	VLITE
Bronze	scalar	Visual*	NONE	NONE	NONE	NONE

CONTAMINATION

There is no indication of any contamination in the oil.


Silicium	ppm	ASTM D5185(m)	>20	13	17	14
Potassium	ppm	ASTM D5185(m)	>20	<1	0	<1
L'eau		WC Method	>0.2	NEG	NEG	NEG
Limon	scalar	Visual*	NONE	NONE	NONE	NONE
Débris	scalar	Visual*	NONE	NONE	NONE	NONE
Saleté	scalar	Visual*	NONE	VLITE	NONE	NONE
Apparence	scalar	Visual*	NORML	NORML	NORML	NORML
Odeur	scalar	Visual*	NORML	NORML	NORML	NORML
Eau émulsifiée	scalar	Visual*	>0.2	NEG	NEG	NEG

ÉTAT DU FLUIDE


The condition of the oil is acceptable for the time in service (unconfirmed).

Sodium	ppm	ASTM D5185(m)		<1	<1	<1
Bore	ppm	ASTM D5185(m)		<1	0	0
Baryum	ppm	ASTM D5185(m)		0	<1	0
Molybdène	ppm	ASTM D5185(m)		0	0	0
Manganèse	ppm	ASTM D5185(m)		0	0	0
Magnésium	ppm	ASTM D5185(m)		<1	0	0
Calcium	ppm	ASTM D5185(m)		<1	<1	0
Phosphore	ppm	ASTM D5185(m)		423	449	513
Zinc	ppm	ASTM D5185(m)		<1	<1	<1
Soufre	ppm	ASTM D5185(m)		58	68	25
Visc 40°C	cSt	ASTM D7279(m)	142.8	154	154	155


Viscosité 40°C




Alliages ferreux



Métaux non-ferreux



Viscosité 40°C



Laboratoire : WearCheck - C8-1175 Appleby Line, Burlington, ON L7L 5H9
N° d'échantillon : WC0878509
N° de laboratoire : 02624506
Numéro unique : 5749625
Analyse : MAR 1

Reçu : 25 Mar 2024
Tested : 26 Mar 2024
Diagnostiqué : 26 Mar 2024 - Wes Davis

Canadian Coast Guard
 CCGS Amundsen, 101 Boul. Champlain
 Quebec, QC
 CA G1K 7Y7

Contact: Chief Engineer
 amundsense@ccgs-ngcc.gc.ca
 T: (418)953-8233
 F: x:

Pour discuter ce rapport, contacter le service à la clientèle au 1-800-268-2131.
 Test denoted (*) outside scope of accreditation, (m) method modified, (e) tested at external lab.
 La validez de los resultados y la interpretación se basan en la muestra y la información proporcionada.