




PAN PEK DJAKOVO


Customer: PTRHTF40126	System Information	Sample Information
TRIBOTIM D.O.O LITIJSKA CESTA 259 LJUBLJANA - DOBRUNJE, Slovenia Attn: Marjan Leskovar Tel: (003)863-0321003 E-Mail: marjan.leskovar@tribotim.eu	System Volume: 2000 ltr Bulk Operating Temp: Not Specified Heating Source: Blanket: Fluid: SASOL MARLOTHERM SH Make:	Lab No: 02184191 Analyst: Philip Riley Sample Date: 11/08/17 Received Date: 11/27/17 Completed: 08/08/18 To discuss this report contact Philip Riley at (440)124-4378171

Recommendation: Competitor product of unfamiliar chemistry therefore unable to recommend any actions against this product

Comments:



Sample Date	Received Date	Fluid Age	Sample Location	Flash Point (COC)	Water (KF)	Viscosity (40°C)	Acid Number	Solids	GCD 10%	GCD 50%	GCD 90%	GCD % < 335°C
	mm/dd/yy			°F/°C	ppm	cSt	mg/KOH/g	%wt	°F/°C	°F/°C	°F/°C	%
11/08/17	11/27/17	10y		410 / 210	49.6	19.1	0.007	0.033	697 / 370	726 / 386	744 / 395	1.27
Baseline Data				266 / 130		17	0.03		703 / 373		739 / 393	0.0





Sample Date	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc	
11/08/17	0	0	0	0	0	0	0	0	0	0	0	1	0	0	0	0	0	0	0	0	0	0	0	0	0
Baseline Data			0	0						0			0	0					0				0		

Elemental analysis results (above) in parts per million (ppm). [10,000 ppm = 1.0%]



Historical Comments

Petro-Canada makes no representation or warranty of any kind, either express or implied, as to the accuracy or completeness of the analysis and assumes no responsibility and shall have no liability whatsoever with respect to such analysis, or a party's use of it. Petro-Canada is a division of HollyFrontier Corporation.