




PAN PEK DOO CROATIA



Customer: PTRHTF40126	System Information	Sample Information
TRIBOTIM D.O.O LITIJSKA CESTA 259 LJUBLJANA - DOBRUNJE, Slovenia Attn: Marjan Leskovar Tel: (003)863-0321003 E-Mail: marjan.leskovar@tribotim.eu	System Volume: 10000 ltr Bulk Operating Temp: Not Specified Heating Source: Blanket: Fluid: SASOL MARLOTHERM SH Make:	Lab No: 02267317 Analyst: Philip Riley Sample Date: 02/07/19 Received Date: 02/12/19 Completed: 02/19/19

Recommendation: Competitor product and cannot make informed recommendation

Comments: (GCD) 90% Distillation Point is marginally low.



Sample Date	Received Date	Fluid Age	Sample Location	Flash Point (COC)	Water (KF)	Viscosity (40°C)	Acid Number	Solids	GCD 10%	GCD 50%	GCD 90%	GCD % < 335°C
	mm/dd/yy			°F/°C	ppm	cSt	mg/KOH/g	%wt	°F/°C	°F/°C	°F/°C	%
02/07/19	02/12/19	0y	PAN23456 4231498	428 / 220	41.8	20.6	0.041	0.019	668 / 353	693 / 367	713 / 379	1.82
Baseline Data				266 / 130		17	0.03		703 / 373		739 / 393	0.0





Sample Date	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc	
02/07/19	3	0	0	0	0	0	0	0	0	0	0	10	0	0	0	0	0	0	0	0	0	0	0	0	0
Baseline Data			0	0						0			0	0					0				0		

Elemental analysis results (above) in parts per million (ppm). [10,000 ppm = 1.0%]



Historical Comments

Petro-Canada makes no representation or warranty of any kind, either express or implied, as to the accuracy or completeness of the analysis and assumes no responsibility and shall have no liability whatsoever with respect to such analysis, or a party's use of it. Petro-Canada is a division of HollyFrontier Corporation.