




ECOPTOH1450



Customer: PTRHTF40037	System Information	Sample Information
KATJANG PEDIC P.C.I BV MARKT 30 ZEELAND SINT MAARTENSDIHK, ZEE NETHERLANDS Attn: Maintenance Manager Tel:	System Volume: 3200 ltr Bulk Operating Temp: 527F / 275C Heating Source: Blanket: Fluid: PETRO CANADA PURITY FG HEAT TRANSFER FLUID Make: ECO PROCESSTECHNIK	Lab No: 02375854 Analyst: Matthias Voss Sample Date: 09/04/20 Received Date: 09/15/20 Completed: 10/06/20 Matthias Voss Matthias.Voss@petrocanadalsp.com

Recommendation: Possible contamination (Top up) with different, not suitable fluid. Try to figure out reason for abnormal high TAN and Zinc parameters. Other properties are in a proper manner and if differing values are explainable, fluid is suitable for further use.

Comments: Acid Number (AN) is severely high. Zinc ppm levels are severely high.




Sample Date	Received Date	Fluid Age	Sample Location	Flash Point (COC)	Water (KF)	Viscosity (40°C)	Acid Number	Solids	GCD 10%	GCD 50%	GCD 90%	GCD % < 335°C
	mm/dd/yy			°F/°C	ppm	cSt	mg/KOH/g	%wt	°F/°C	°F/°C	°F/°C	%
09/04/20	09/15/20	54m		457 / 236	71.8	33.6	0.83	0.216	719 / 382	810 / 432	906 / 485	1.43
04/16/20	04/28/20	2m		432 / 222	13.1	34.7	0.76	0.096	725 / 385	811 / 433	904 / 485	0.51
03/05/20	03/11/20	1m		439 / 226	40.7	34.8	0.951	0.296	719 / 382	802 / 428	901 / 483	0.00
Baseline Data				459 / 237		37.12	0.90		721 / 383	807 / 431	892 / 478	1.5





Sample Date	Iron	Chromium	Nickel	Aluminum	Copper	Lead	Tin	Cadmium	Silver	Vanadium	Silicon	Sodium	Potassium	Titanium	Molybdenum	Antimony	Manganese	Lithium	Boron	Magnesium	Calcium	Barium	Phosphorus	Zinc
09/04/20	21	0	0	0	1	0	0	0	0	0	2	0	0	0	0	0	0	0	0	0	0	2	42	121
04/16/20	5	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	14	0
03/05/20	72	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	28	0
Baseline Data			0	0						0			0	0				0	0				230	

Elemental analysis results (above) in parts per million (ppm). [10,000 ppm = 1.0%]



Historical Comments	
04/16/20	All parameters meet specification, fluid fit for further use and re-sample at normal frequency
03/05/20	Product tests to specification and all within the normal range. Fluid fit for further use, please re-sample at normal frequency, likely 12 months

Petro-Canada makes no representation or warranty of any kind, either express or implied, as to the accuracy or completeness of the analysis and assumes no responsibility and shall have no liability whatsoever with respect to such analysis, or a party's use of it. Petro-Canada is a division of HollyFrontier Corporation.